



## DOWANOL DPM

Dipropylene Glycol Methyl Ether

### **CH<sub>3</sub>O[CH<sub>2</sub>CH(CH<sub>3</sub>)O]<sub>2</sub>H (One of several isomers)**

**A hydrophilic glycol ether with a moderate evaporation rate and excellent coupling abilities**

### Introduction

DOWANOL\* DPM glycol ether is a mid-to slow evaporating solvent. This hydrophilic solvent has 100% water solubility and is ideally suited as a coupling agent in a wide range of solvent systems. DOWANOL DPM glycol ether has a higher flash point than DOWANOL PM glycol ether making it easier to handle, store, and ship. Often incorporated into latex emulsion coatings DOWANOL DPM glycol ether can be used to prevent shocking (coagulation of emulsion) when hydrophobic solvents are used. More broadly, its hydrophilic nature makes it an ideal coupling aid in water reducible coatings, and cleaning applications. DOWANOL DPM glycol ether's intermediate evaporation rate allow it to be used in a potentially wider range of systems than many other solvents.

### Physical properties†

Molecular weight (g/mol)		148.2
Boiling point @ 760 mmHg, 1.01 bar	374°F	190°C
Flash point (Setaflash Closed Cup)	167°	75°C
Freezing point	-117°F	-83°C
Vapor pressure@ 20°C — extrapolated		0.28 mmHg 0.37 mbar
Specific gravity (25/25°C)		0.951
Density @ 20°C	7.95 lb/gal	0.953 g/cm <sup>3</sup>
@ 25°C	7.91 lb/gal	0.948 g/cm <sup>3</sup>
Viscosity (cP or mPa·s @ 25°C)		3.7
Surface tension (dynes/cm or mN/m @ 25°C)		28.8
Specific heat (J/g°C @ 25°C)		2.25
Heat of vaporization (J/g) at normal boiling point		267
Net heat of combustion (kJ/g) — predicted @ 25°C		27.2
Autoignition temperature	405°F	207°C
Evaporation rate	(n-butyl acetate = 1.0) (diethyl ether = 1.0)	0.035 351
Solubility, g/100 g @ 25°C		
Solvent in water		
Water in solvent		

Hansen solubility parameters (J/cm <sup>3</sup> ) <sup>1/2</sup>	
_d (Dispersion)	15.5
_p (Polar)	4.0
_h (Hydrogen bonding)	11.5
Flammable limits (vol. % in air)	
Lower (measured @ 100°C)	1.10
Upper (measured @ 150°C)	14.00

†The physical property data listed here are considered to be typical properties, not specifications.

## Classification/Registry Numbers††

CAS Number	34590-94-8
AICS (Australia)	34590-94-8
DSL (Canada)	34590-94-8
ECL (Korea)	2-272
EINECS (EU)	252-104-2
MITI (Japan)	2-426
TSCA (U.S.)	34590-94-8

†† **NOTE:** Classifications apply only to this glycol ether product. It is the responsibility of the formulator to ensure that the final finished product complies with the regulations of a given country prior to its sale or distribution in that country.

## Suggested Applications

- Coupling agent (often in blends) for water-based dilutable coatings.
- Active solvent for solvent-based coatings.
- Coupling agent and solvent in household and industrial cleaners, grease and paint removers, metal cleaners, and hard surface cleaners.
- Tail solvent for solvent-based gravure and flexographic printing inks.
- Primary solvent in solvent-based silk screen printing inks.
- Coupling agent in solvent blends for water-based gravure, flexographic, and silk screen printing inks.
- Coupling agent and solvent for vat dyeing fabrics.
- Mutual solvent, coupling agent, and emollient in cosmetic formulations.
- Stabilizer for agricultural herbicides.
- Coalescent for floor polishes and finishes

## Features

- Powerful solvency
- Moderate evaporation rate
- Low viscosity
- High dilution ratio
- Low surface tension
- Coupling ability
- Wide range of applications

**NOTE:** Consult the appropriate Material Safety Data Sheet for safety and handling guidelines for this product.

\*The Dow Chemical Company  
Midland, Michigan 48674 U.S.A.

In The United States And Canada:  
1-800-447-4369  
Fax: 1-989-832-1465

In Europe: +800 3 694 6367  
Toll Phone: +32 3 450 2240  
Toll Fax: +32 3 450 2815

In The Pacific: +800 7776 7776  
Fax: +800 7779 7779  
In Other Global Areas: 1-989-832-1556  
Fax: 1-989-832-1465

**Notice:** No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

Published March 2004

