



## Technical Data Sheet

### DOWSIL™ ME-1030 Adhesive Clear

DOWSIL™ ME-1030 Adhesive Clear is a one-part, translucent, thixotropic adhesive with self-priming adhesion.

#### Features & Benefits

- Very low Young's modulus
- Highly stress relieving

#### Applications

- Pressure Sensor
- CCD
- SAW filter

#### Application Methods

- Automated or manual needle dispense

#### Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

Property	Unit	Result
Viscosity	cP	7300
	mPa-sec	7300
	Pa-sec	7.3
Thixotropy	NA	1.8
Working Time - Viscosity Rise, 24 hrs at 25°C	%	113
Rheometer T90 Cure Time @ 180°C	seconds	15
Tensile Strength	psi	115
	MPa	0.8
	kg/cm <sup>2</sup>	8
Elongation	%	240
Young's Modulus	psi	130
	MPa	0.9
	kg/cm <sup>2</sup>	9
Durometer Shore A (JIS) <sup>1</sup>		31

1. JIS: Japanese Industrial Standard.

## Typical Properties (Cont.)

Property	Unit	Result
Unprimed Adhesion - Lap Shear to Aluminum	psi	80
	MPa	0.6
	N/cm <sup>2</sup>	57
Dielectric Strength (JIS K 6249)	Volts/mil	625
	kV/mm	25
Dielectric Constant @ 1 MHz (JIS K 6249)		2.8
Dissipation Factor @ 1 MHz (JIS K 6249)		0.0008
Volume Resistivity (JIS K 6249)	ohm*cm	2.7E+16
Linear CTE (by TMA)	ppm/°C	300
Thermal Conductivity	btu/hr ft °F	0.092
	W/mK	0.16
Impurity (Na+)	ppm	< 2
Impurity (K+)	ppm	< 2
Impurity (Cl-)	ppm	< 1.5

### Description

Dow silicone microelectronics adhesive products are designed to meet key criteria in the micro- and optoelectronic packaging industry, including high purity, moisture resistance and thermal and electrical stability. Dow silicone microelectronics adhesive products deliver outstanding stress relief and high-temperature stability, with excellent primerless adhesion to a wide range of substrate materials and components. These products are ideally suited for microelectronic devices requiring low-modulus materials, for lead-free solder reflow temperatures (260°C), or other high-reliability applications. With both wet dispensed and pre-cured film product forms available these materials meet a wide range of needs for device packaging applications. Dow silicone microelectronics adhesive products are supplied as convenient, one-part materials, with specific formulations developed for electrical conductivity, electrical insulation or thermal conductivity, all of which cure via heat without byproducts.

### Preparing Surfaces

All surfaces should be thoroughly cleaned and/or degreased with solvents such as DOWSIL™ OS fluids, naphtha, mineral spirits, or methyl ethyl ketone (MEK). Light surface abrasion is recommended whenever possible, because it promotes good cleaning and increases the surface area for bonding. A final surface wipe with acetone or IPA is also useful to remove residues that may be left behind by other cleaning methods. On some surfaces, different cleaning techniques will give better results than others. Users should determine the best techniques for their applications.

### Substrate Testing

Due to the wide variety of substrate types and differences in substrate surface conditions, general statements on adhesion and bond strength are impossible. To ensure maximum bond strength on a particular substrate, 100 percent cohesive failure of the adhesive in a lap shear or similar adhesive strength is needed. This ensures compatibility of the adhesive with the substrate being considered. Also, this test can be used to determine minimum cure time or to detect the presence of surface contaminants such as mold release agents, oils, greases and oxide films.

**Compatibility**

Certain materials, chemicals, curing agents and plasticizers can inhibit the cure of addition cure adhesives. Most notable of these include: organotin and other organometallic compounds, silicone rubber containing organotin catalyst, sulfur, polysulfides, polysulfones or other sulfur containing materials, unsaturated hydrocarbon plasticizers, and some solder flux residues. If a substrate or material is questionable with respect to potentially causing inhibition of cure, it is recommended that a small scale compatibility test be run to ascertain suitability in a given application. The presence of liquid or uncured product at the interface between the questionable substrate and the cured gel indicates incompatibility and inhibition of cure.

**Repairability**

Removal of Dow electronic materials to allow for failure analysis can be assisted with DOWSIL™ OS fluids. Additional information regarding these products is available from Dow.

**Handling  
Precautions**

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

**Usable Life and  
Storage**

Shelf life is indicated by the "Use By" date found on the product label. For best results, Dow lid seal adhesives should be stored at or below the maximum specified storage temperature. Special precautions must be taken to prevent moisture from contacting these materials. Containers should be kept tightly closed and head or air space minimized. Partially filled containers should be purged with dry air or other gases, such as nitrogen. Any special storage and handling instructions will be printed on the product containers.

**Packaging  
Information**

Material should be stored at the recommended condition, -10 to -25°C, immediately upon arrival. Repeated freezing and thawing should be avoided. To prepare a syringe of material for use, allow the syringe to sit at least one hour at room temperature without opening the plastic bag.

**Limitations**

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

**Health and  
Environmental  
Information**

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, [dow.com](http://dow.com) or consult your local Dow representative.

**Disposal  
Considerations**

Dispose in accordance with all local, state (provincial) and federal regulations. Empty containers may contain hazardous residues. This material and its container must be disposed in a safe and legal manner.

It is the user's responsibility to verify that treatment and disposal procedures comply with local, state (provincial) and federal regulations. Contact your Dow Technical Representative for more information.

## **Product Stewardship**

Dow has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Dow products - from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

## **Customer Notice**

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

## **How Can We Help You Today?**

Tell us about your performance, design, and manufacturing challenges. Let us put our silicon-based materials experience, application knowledge, and processing experience to work for you.

**For more information** about our materials and capabilities, visit **dow.com**.

To discuss how we could work together to address your specific needs, go to **dow.com** for a contact close to your location. Dow has customer service teams, science and technology centers, application support teams, sales offices, and manufacturing sites around the globe.

dow.com

**NOTICE:** No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

