

Technical Data Sheet

CARBOWAX™ SENTRY™ Polyethylene Glycol (PEG) 3350 (Inhibited)

Product(s) CARBOWAX™ SENTRY™ Polyethylene Glycol 3350 USP Flake (Inhibited); Macrogol 3350

Ph. Eur.

CARBOWAX™ SENTRY™ Polyethylene Glycol 3350 USP Granular (Inhibited); Macrogol

3350 Ph. Eur.

CARBOWAX™ SENTRY™ Polyethylene Glycol 3350 USP Powder (Inhibited); Macrogol

3350 Ph. Eur.

CARBOWAX™ SENTRY™ Polyethylene Glycol 3350 USP Molten (Inhibited)

Description Polyethylene Glycol

CAS Number 25322-68-3

Applications Adhesives

Chemical Intermediates

Dye Carrier

Excipient: Ointments and Creams, Tablet Binder and Coating

Personal Care Plasticizer

Typical Physical Properties(1)

	Value
Property	
Physical Form	Waxy solid
Average Number of Repeating Oxyethylene Units	76
Range of Average Molecular Weight	3015 – 3685
Range of Average Hydroxyl Number, mg KOH/g	30 – 38
Density, g/cm ³ at 60°C	1.093
Melting or Freezing Range, °C	53 – 57
Solubility in Water at 20°C, % by weight	67
Viscosity at 100°C, cSt	90.8
Heat of Fusion, Cal/g	39

^{1.} Typical properties, not to be construed as specifications

Form No. 118-01815-01-0324 DOW

US

Toll Free 800 441 4DOW

989 832 1542

International

Europe/Middle East +800 800 36 94 63 67

Italy +800 783 825 Asia/Pacific +800 77 76 7776 +60 37 958 3392

South Africa +800 99 5078

http://www.dow.com/

Notice: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the Customer is responsible for determining whether products and the information in this document are appropriate for the Customer's use and for ensuring that the Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Dow assumes no obligation or liability for the information in this document. No warranties are given; all implied warranties of merchantability or fitness for a particular purpose are expressly excluded. This document is intended for global use.

