



## Technical Data Sheet

### DOWSIL™ 40-001 Additive

#### Organo-functional siloxane

#### Features & Benefits

- Anti-drip additive or synergist
- Flame retardant
- Thinner clear polycarbonate applications
- 100% non-halogenated silicone polymer
- Active at low use level

#### In polycarbonate compounds:

- Reaches UL 94 V-0 rating at 1 mm with synergists
- Reaches UL 94 V-0 at 1.5 mm
- Efficiency at low loading
- Keeps transparency of polycarbonate
- Haze at 2%
- No impact on Young's modulus and tensile maximum force at traction.

#### Composition

- Organo-functional liquid siloxane
- 100% active

#### Applications

- Plastics additive used as flame retardant for polycarbonate where high transparency is required
- Consumer electronics: General LED lighting
- Automotive: Lens covers for next-generation electric vehicles
- Outdoor lighting: Electrical components and insulation

#### Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

Test <sup>1</sup>	Property	Unit	Result
	Physical Form	NA	Transparent Liquid
CTM 0006-A	Flash Point Cleveland Open Cup	°C	> 110

1. CTM = Corporate Test Method

UNRESTRICTED – May be shared with anyone

™Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow

DOWSIL™ 40-001 Additive

© 2017 The Dow Chemical Company. All rights reserved.

**Description** DOWSIL™ 40-001 Additive is a liquid organo-functional siloxane recommended as additive for polycarbonate. This product has an excellent miscibility with polycarbonate matrix. Benefits includes improvement of flame retardancy performances (anti-dripping and flaming time reduction) while maintaining transparency with low haziness of the final polycarbonate compound. DOWSIL 40-001 Additive is suitable for use under the processing windows of polycarbonate.

**How To Use** Typical recommended usage levels of DOWSIL 40-001 Additive ranges from 1.5 up to 4 wt% based on total formulation. Test performed on typical extrusion polycarbonate grade (MFI 11) demonstrate at a 2 wt% loading following benefits:

- UL 94 V-0 rating at 1.5 mm
- UL 94 V-0 rating possible at 1 mm when used with synergists
- Total transmittance kept at 87% (against 89% for neat PC)
- Haze at 2%
- No impact on Young-Modulus and maximum tensile strength

It is recommended to process DOWSIL 40-001 Additive through twin screws extrusion melt blending. The additive can rather be introduced through an adsorption on PC pellets and more recommended through a direct liquid injection in the molten polymer right after the melting zone.

It is recommended to perform some preliminary tests to determine the optimum loading and mixing conditions to reach desired performances.

Table 1: Formulation<sup>1</sup>:

	DOWSIL 40-001 Additive	KSS	PTFE
Form 1	0	0	0
Form 2	2	0	0
Form 3	2	0.6	0
Form 4	4	0	0
Form 5	4	0.6	0
Form 6	0	0.6	0.3

1. All formulations were performed using clear polycarbonate, MFI 11 (300°C; 1.2 kg). All formulations were performed using a TSE 20 mm diameter and L/D 40. Introduction of polycarbonate pellets made in 10D. DOWSIL 40-001 Additive addition through direct liquid injection in 20D. Formulation 1 represents the neat PC, while form 6 represents a typical V-0 formulation using PTFE and KSS as FR package.

Table 2: Processing conditions:

Temperature (°C)	285	280	275	260	260
Screw Speed (rpm)			200		
Throughput (kg/h)			2.0		

UNRESTRICTED – May be shared with anyone

®™ Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow

DOWSIL™ 40-001 Additive

© 2017 The Dow Chemical Company. All rights reserved.

Table 3: Test Results:

Sample ID	UL 94 1.5 mm		UL 94 1 mm		Optical ASTM D-1003 (1.5 mm)		Mechanical ISO 527-2		
	Ranking	t1(s)	t2 (s)	Ranking	Tt (%)	Haze (%)	E-Mod	F Max	Elongation @ Break (%)
Form 1	V-2	10,0	11,4		89	0	2400	64	106
Form 2	V-0	3,0	1,4		87	2.4	2350	65	55
Form 3	V-0	2,4	4,4	V-1	87	2.8	2360	66	70
Form 4	V-0	3,2	2,4	HB	87	1.4	2390	67	71
Form 5	V-0	2,8	1,0	V-0	85	2.5	2410	68	46
Form 6	V-0	8.6	7	V-2	81	16	2320	63	76

Results show the V-0 rating obtained on formulations containing DOWSIL 40-001 Additive. Compared to PTFE/KSS formulation, the use of DOWSIL 40-001 Additive allowed maintaining initial optical performances with very limited impact. DOWSIL 40-001 Additive also demonstrated limited impact on mechanical performance.

#### Handling Precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT [WWW.CONSUMER.DOW.COM](http://WWW.CONSUMER.DOW.COM), OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

#### Usable Life And Storage

When stored in unopened original container at a maximum temperature of 30°C, DOWSIL 40-001 Additive has a usable lifetime of 12 months.

#### Packaging Information

DOWSIL 40-001 Additive is available in 18 kg pails or 225 kg drums.

#### Limitations

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

#### Health And Environmental Information

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, [www.consumer.dow.com](http://www.consumer.dow.com) or consult your local Dow representative.

UNRESTRICTED – May be shared with anyone

®™ Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow

DOWSIL™ 40-001 Additive

© 2017 The Dow Chemical Company. All rights reserved.

<http://www.consumer.dow.com>

**LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY**

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

**TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DOW SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.**

**DOW DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.**

