



RHOPLEX™ 3829 Floor Finish Polymer

Features & Benefits

- Improved floor appearance – Polishes based on RHOPLEX™ 3829 Floor Finish Polymer offer brighter and cleaner looking floors relative to traditional polishes.
- Reduced labor costs – Polishes based on RHOPLEX™ 3829 Polymer are brighter and appear cleaner than conventional polishes. Consequently, the cycle time for detergent scrubbing, recoat and stripping is longer for RHOPLEX™ 3829 Polymer based finishes resulting in lower maintenance costs.
- Foam control—Since RHOPLEX™ 3829 Polymer is a low foaming polymer, properly formulated polishes made with RHOPLEX™ 3829 Polymer exhibit less foam in the bucket and during application than most conventional polishes.

Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

Property	Unit	Result
Appearance		Milky-white liquid
Solids content	%	38
Minimum Film-Formation Temperature (MFFT)	°C	~70
pH		~8.5
Viscosity (Brookfield LVT, #1 Spindle, 60 rpm)	cP	< 100
Density @ 25°C	Lb/U.S. gal	~8.5
Specific Gravity		1.06
Ionic Charge		Anionic
Freeze/Thaw Stability	cycles	≥ 3

Description

RHOPLEX™ 3829 Polymer is a highly durable low foaming, metal crosslinked, modified acrylic polymer that employs patented optically brightening technology. Polishes based on RHOPLEX™ 3829 Polymer brighten and optically enhance the natural appearance of the floor. These polishes are particularly well suited for high profile floors, where high gloss and durability are desirable. Supermarkets, retail stores, hospitals and schools, are good examples of this type of application.

Performance Characteristics

As with all Dow floor polish polymers, RHOPLEX™ 3829 Polymer shares a number of common performance characteristics.

The suggested polish formulations made with RHOPLEX™ 3829 Polymer meet or exceed the industry slip resistance standard as tested by the ASTM D-2047 Standard Test Method. These finishes can be formulated to a range of solid levels from 15 to 25 percent. RHOPLEX™ 3829 Polymer offers for the manufacture of polishes that can be applied at floor temperatures of 50°F (10°C) and above.

RHOPLEX™ 3829 Polymer Formulation N-29-3

Formulation N-29-3 is a suggested starting point formulation that offers excellent lay down gloss and very good burnish response and wear performance properties. N-29-3 is formulated with RHOPLEX™ 1531C Emulsion, a high gloss, all-acrylic, alkali-soluble emulsion, which imparts excellent leveling characteristics.

Material in Proper Order of Addition	Percent by Weight	Lb./100 U.S. Gal.	Gal./100 U.S. Gal.
Water	41.92	358.88	42.99
KATHON™ CG/ICP preservative	0.04	0.34	0.04
Capstone FS-65 fluorosurfactant ¹	0.04	0.31	0.04
CARBITOL™ Solvent - low gravity	4.81	41.15	4.98
DOWANOL™ DPM Glycol Ether	0.95	8.13	1.02
UCAR™ Filmer IBT Coalescent	1.19	10.19	1.28
Tri(butoxyethyl) phosphate plasticizer	1.46	12.49	1.47
RHOPLEX™ 3829 Polymer (38%)	40.43	346.14	38.89
RHOPLEX™ 1531C Emulsion (38%) ²	3.41	29.17	3.31
A-C 540N ethylene-acrylic copolymer (30%) ³	3.09	26.43	3.21
A-C 325N polypropylene polymer (35%) ⁴	2.65	22.67	2.73
Defoamers ⁵	0.02	0.17	0.02
Totals	100.00	856.06	100.00
Formulation Constants	Theoretical Non-Volatile Solids		20%
	Theoretical Density, Lb/U.S. Gal		~8.6
	Polymer/ASE/Wax Ratio 82/5/13		83/7/10

1. Recommended Wetting Agent: Capstone FS-65
2. Alternative ASRs: Michem Dispersion MD-91530 (30%) and Chemrez 30 (30%)
3. Commercial Trade Names: Michem Emulsion 44730 (30%) and BYK Wax emulsion Aquacer 8840 (40%)
4. Commercial Trade Names: Michem Emulsion 93235 (35%) and BYK Wax emulsion Aquacer 8959 (35%)
5. Recommended Defoamer: DEE FO P140 Münzing, info@münzing.us

RHOPLEX™ 3829 Polymer Formulation N-29-4

Formulation N-29-4 is a suggested starting point formulation that offers excellent laydown gloss and very good burnish response and wear performance properties. N-29-4 similar to formulation N-29-3 but formulated with a solution ASR.

Material in Proper Order of Addition	Percent by Weight	Lb./100 U.S. Gal.	Gal./100 U.S. Gal.
Water	44.65	382.45	45.84
KATHON™ CG/ICP preservative	0.04	0.35	0.04
Capstone FS-65 fluorosurfactant ¹	0.04	0.33	0.04
CARBITOL™ Solvent - low gravity	4.83	41.36	5.00
DOWANOL™ DPM Glycol Ether	0.93	7.98	1.00
Benzoflex 50	0.93	7.98	0.85
Tri(butoxyethyl) phosphate plasticizer	1.45	12.40	1.46
RHOPLEX™ 3829 Polymer (38%)	40.28	344.96	38.76
Alkali solution resin (30%) ²	1.39	11.90	1.35
A-C 540N ethylene-acrylic copolymer (30%) ³	2.51	21.52	2.59
A-C 325N polypropylene polymer (35%) ⁴	2.93	25.11	3.05
Defoamers ⁵	0.02	0.17	0.02
Totals	100.00	856.51	100.00
Formulation Constants			
	Theoretical Non-Volatile Solids		20%
	Theoretical Density, Lb/U.S. Gal		~8.6
	Polymer/ASE/Wax Ratio 82/5/13		87/3/10

1. Recommended Wetting Agent: Capstone FS-65
2. Alternative ASRs: Michem Dispersion MD-91530 (30%) and Chemrez 30 (30%)
3. Commercial Trade Names: Michem Emulsion 44730 (30%) and BYK Wax emulsion Aquacer 8840 (40%)
4. Commercial Trade Names: Michem Emulsion 93235 (35%) and BYK Wax emulsion Aquacer 8959 (35%)
5. Recommended Defoamer: DEE FO P140 Münzing, info@munzing.us

Handling Precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

Usable Life and Storage

Store products in tightly closed original containers at temperatures recommended on the product label.

Limitations

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

Health and Environmental Information

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, dow.com or consult your local Dow representative.

Disposal Considerations

Dispose in accordance with all local, state (provincial) and federal regulations. Empty containers may contain hazardous residues. This material and its container must be disposed in a safe and legal manner.

It is the user's responsibility to verify that treatment and disposal procedures comply with local, state (provincial) and federal regulations. Contact your Dow Technical Representative for more information.

Product Stewardship

Dow has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Dow products - from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

dow.com

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

