



Technical Data Sheet

DOW™ HDPE DGDB-2480 NT High Density Polyethylene Resin

Overview

DOW™ DGDB-2480 NT High Density Polyethylene Resin is produced using UNIPOL™ process technology. It is intended for use in pipe applications where long term hydrostatic strength and resistance to slow crack growth are desired. Suitable applications include natural gas distribution pipes, large diameter industrial piping, mining, sewage, and municipal water service lines.

Industrial Standards Compliance:

- ASTM D 3350: cell classification
 - Natural - PE345464A
 - Black - PE345464C (See NOTES A)
- Plastics Pipe Institute (PPI): TR-4
 - Natural Pipe - DGDB-2480 NT 3408
 - ASTM PE3608 pipe grade - 1600 psi HDB @ 73°F
 - Black Pipe - DGDB-2480 BK 3408 (See NOTES B)
 - ASTM PE3608 pipe grade - 1600 psi HDB @ 73°F and 800 psi HDB @ 140°F
 - NSF International
 - NSF/ANSI Standard 14
 - NSF/ANS/CAN Standard 61
 - Natural Pipe - DGDB-2480 NT 3608
 - Black Pipe - DGDB-2480 BK 3608 (See NOTES B)

Consult the regulations for complete details.

NOTES:

- A. The first five numbers of the cell classification are based on natural resin. The last number and letter are based on black resin (natural resin plus 6.5% DFNF-0092).
- B. Natural resin extruded under proper conditions with carbon black masterbatch DFNF-0092 (6.5%).

Additive

- Antiblock: No
- Slip: No
- Processing aid: No

Properties

Physical	Nominal Value	Unit (English)	Nominal Value	Unit (SI)	Test Method ¹
Density ²					ASTM D792
	0.944	g/cm ³	0.944	g/cm ³	
	0.954	g/cm ³	0.954	g/cm ³	
Melt Index					ASTM D1238
190°C/2.16 kg	0.10	g/10 min	0.10	g/10 min	
190°C/21.6 kg	8.3	g/10 min	8.3	g/10 min	
Mechanical					
Tensile Strength ³ (Yield)	3200	psi	22.1	MPa	ASTM D638
Tensile Elongation ³ (Break)	850	%	850	%	ASTM D638
Flexural Modulus ^{3,4}	120000	psi	827	MPa	ASTM D790B
Slow Crack Growth PENT ⁵ (176°F (80°C))	200	hr	200	hr	ASTM F1473
Impact					
Notched Izod Impact ³ (73°F (23°C))	4.0	ft-lb/in	210	J/m	ASTM D256A
Thermal					
Brittleness Temperature ³	< -148	°F	< -100	°C	ASTM D746A
Thermal Stability	> 482	°F	> 250	°C	ASTM D3350
Extrusion					
Melt Temperature	380 to 440	°F	193 to 227	°C	
Extrusion Notes					
Fabrication Conditions:					
<ul style="list-style-type: none"> Screw Type: High quality HDPE (preferably barrier for complete melting) Melt Temperature Range: 380–440°F (193–225°C) 					

1. ASTM: American Society for Testing and Materials
2. Natural resin extruded under proper conditions with carbon black masterbatch DFNF-0092 (6.5%)
3. Compression molded parts prepared according to ASTM D 4703, Procedure C. Properties will vary with changes in molding conditions and aging time. Data generated based on ASTM F1473 at Dow facility. Pent data projected based on representative test samples and conditions.
4. Method I (3 point load)
5. 2.4 MPa

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

Product Stewardship

The Dow Chemical Company and its subsidiaries ("Dow") has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our Product Stewardship program rests with each and every individual involved with Dow products -from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

Medical Applications Policy

NOTICE REGARDING MEDICAL APPLICATION RESTRICTIONS: Dow will not knowingly sell or sample any product or service ("Product") into any commercial or developmental application that is intended for:

- a. long-term or permanent contact with internal bodily fluids or tissues. "Long-term" is contact which exceeds 72 continuous hours;
- b. use in cardiac prosthetic devices regardless of the length of time involved ("cardiac prosthetic devices" include, but are not limited to, pacemaker leads and devices, artificial hearts, heart valves, intra-aortic balloons and control systems, and ventricular bypass-assisted devices);
- c. use as a critical component in medical devices that support or sustain human life; or
- d. use specifically by pregnant women or in applications designed specifically to promote or interfere with human reproduction.

Dow requests that customers considering use of Dow products in medical applications notify Dow so that appropriate assessments may be conducted. Dow does not endorse or claim suitability of its products for specific medical applications. It is the responsibility of the medical device or pharmaceutical manufacturer to determine that the Dow product is safe, lawful, and technically suitable for the intended use. **DOW MAKES NO WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF ANY DOW PRODUCT FOR USE IN MEDICAL APPLICATIONS.**

Contact:
www.dow.com/contact

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the Customer is responsible for determining whether products and the information in this document are appropriate for the Customer's use and for ensuring that the Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Dow assumes no obligation or liability for the information in this document. **NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**

NOTICE: If products are described as "experimental" or "developmental": (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; (3) there is greater potential for Dow to change specifications and/or discontinue production; and (4) although Dow may from time to time provide samples of such products, Dow is not obligated to supply or otherwise commercialize such products for any use or application whatsoever.

NOTICE: This data is based on information Dow believes to be reliable, as demonstrated in controlled laboratory testing. They are offered in good faith, but without guarantee, as conditions and method of use of Dow products are beyond Dow's control. Dow recommends that the prospective user determine the suitability of these materials and suggestions before adopting them on a commercial scale.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability for the accuracy and completeness of such information.

This document is intended for use within Asia Pacific, Latin America, North America

