



Dow ENDURANCE™ DHDA-7708 BK

Semiconductive Linear Low Density Polyethylene Compound for Cable Jacketing

Overview

DOW ENDURANCE™ DHDA-7708 BK is a thermoplastic semiconductive compound specifically designed for jacketing over medium, high, and extra-high voltage power cables. It combines the excellent physical properties and low moisture vapor transmission normally associated with Dow insulating jacket materials with the conductivity of thermoplastic semiconductive insulation shielding compounds. In medium voltage cable applications, a semiconductive jacket provides cable endurance and prolongs cable life by reducing neutral-to-ground impulse voltage. The semiconductive jacket enables on-reel cable diagnostic analysis in high and extra-high voltage applications.

Compared to conventional thermoplastic semiconductive materials, DOW ENDURANCE™ DHDA-7708 BK offers:

- Improved environmental stress-crack resistance
- Improved low-temperature properties
- Improved thermomechanical properties
- Reduced adhesion to strippable insulation shields
- Improved cut-through and abrasion resistance
- Reduced moisture vapor transmission

Details are shown in Figures 1 to 4

Specifications

Cables jacketed with DOW ENDURANCE™ DHDA-7708 BK, prepared using sound commercial fabrication practice, would be expected to meet the following specifications:

- AEIC: CS8, CS9
- ICEA: S-94-649 Type 1, S-108-720 Type 1
- IEC: 60502, 60840, 62067

Additive

- Antiblock: No
- Slip: No
- Processing Aid: No

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.980 g/cm ³	0.980 g/cm ³	ASTM D1505
Environmental Stress-Cracking Resistance (ESCR)			ASTM D1693
10% Igepal, F0	> 500 hr	> 500 hr	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus - Secant	50000 psi	345 MPa	ASTM D638
Tensile Strength	1700 psi	11.7 MPa	ASTM D638
Tensile Elongation (Break)	450 %	450 %	ASTM D638
Films	Nominal Value (English)	Nominal Value (SI)	Test Method
Water Vapor Transmission Rate			ASTM F1249
100°F (38°C), 90% RH	0.097 g/100 in ² /24 hr	1.5 g/m ² /24 hr	
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness (Shore D)	55	55	ASTM D2240
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Brittleness Temperature			ASTM D746
-- 1	-94.0 °F	-70.0 °C	
-- 2	-58.0 °F	-50.0 °C	
Heat Distortion (ICEA) ³ (194°F (90°C))	1.0 %	1.0 %	ASTM D2632
Aging	Nominal Value (English)	Nominal Value (SI)	Test Method
Retention of Tensile Elongation - 1 week			ASTM D638
212°F (100°C)	75 %	75 %	
Retention of Tensile Strength - 1 week			ASTM D638
212°F (100°C)	75 %	75 %	

Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Volume Resistivity			ASTM D991
73°F (23°C)	25 ohms·cm	25 ohms·cm	
194°F (90°C)	50 ohms·cm	50 ohms·cm	

Additional Information

Nominal property values above represent tests on molded, stress-relieved slabs. Cure times were 15 minutes at 175°C.

Figure 1: Low-Temperature Properties - Notched LTB (50% Failure)




Figure 2: Moisture Vapor Transmission - ASTM E 96 (100°F [38°C], 90% RH)




Figure 3: Abrasion Resistance - ASTM 1242 (% Weight Loss/500 Cycles)





Figure 4: Cut-Through Resistance

Extrusion	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	154 to 176 °F	68 to 80 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Melt Temperature	424 to 475 °F	218 to 246 °C

Extrusion Notes

For optimum extrusion results with DOW ENDURANCE™ DHDA-7708 BK, use melt extrusion temperatures in the 425 to 475°F (218 to 246°C) range. Optimum radial resistivity results have been obtained by maximizing the air gap (distance from extrusion die to cooling water). Specific processing conditions can be determined only by trial on individual equipment. Pre-extrusion dehumidified hopper drying for 2 to 4 hours in the range of 155 to 175°F (68 to 80°C) to remove moisture is recommended.

Notes

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

¹ F50

² Notched

³ plaque

Product Stewardship

The Dow Chemical Company and its subsidiaries ("Dow") has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our Product Stewardship program rests with each and every individual involved with Dow products — from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

Medical Applications Policy

NOTICE REGARDING MEDICAL APPLICATION RESTRICTIONS: Dow will not knowingly sell or sample any product or service ("Product") into any commercial or developmental application that is intended for:

- long-term or permanent contact with internal bodily fluids or tissues. "Long-term" is contact which exceeds 72 continuous hours;
- use in cardiac prosthetic devices regardless of the length of time involved ("cardiac prosthetic devices" include, but are not limited to, pacemaker leads and devices, artificial hearts, heart valves, intra-aortic balloons and control systems, and ventricular bypass-assisted devices);
- use as a critical component in medical devices that support or sustain human life; or
- use specifically by pregnant women or in applications designed specifically to promote or interfere with human reproduction.

Dow requests that customers considering use of Dow products in medical applications notify Dow so that appropriate assessments may be conducted. Dow does not endorse or claim suitability of its products for specific medical applications. It is the responsibility of the medical device or pharmaceutical manufacturer to determine that the Dow product is safe, lawful, and technically suitable for the intended use. **DOW MAKES NO WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF ANY DOW PRODUCT FOR USE IN MEDICAL APPLICATIONS.**

Disclaimer

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the Customer is responsible for determining whether products and the information in this document are appropriate for the Customer's use and for ensuring that the Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Dow assumes no obligation or liability for the information in this document. **NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**

NOTICE: If products are described as "experimental" or "developmental": (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; (3) there is greater potential for Dow to change specifications and/or discontinue production; and (4) although Dow may from time to time provide samples of such products, Dow is not obligated to supply or otherwise commercialize such products for any use or application whatsoever.

NOTICE: This data is based on information Dow believes to be reliable, as demonstrated in controlled laboratory testing. They are offered in good faith, but without guarantee, as conditions and method of use of Dow products are beyond Dow's control. Dow recommends that the prospective user determine the suitability of these materials and suggestions before adopting them on a commercial scale.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability for the accuracy and completeness of such information.

Additional Information

North America		Europe/Middle East	+800-3694-6367
U.S. & Canada:	1-800-441-4369		+31-11567-2626
	1-989-832-1426	Italy:	+800-783-825
Mexico:	+1-800-441-4369		
Latin America		South Africa	+800-99-5078
Argentina:	+54-11-4319-0100		
Brazil:	+55-11-5188-9000		
Colombia:	+57-1-219-6000	Asia Pacific	+800-7776-7776
Mexico:	+52-55-5201-4700		+603-7965-5392

www.dowplastics.com

This document is intended for use within Africa & Middle East, Asia Pacific, Europe, Latin America, North America

Published: 2005-11-17

© 2019 The Dow Chemical Company

