



Technical Data Sheet

DOW ENDURANCE™ HFDK-0587 BK

Crosslinkable Semiconductive Shielding Compound

Description

DOW ENDURANCE™ HFDK-0587 BK is a crosslinkable semi-conductive compound based on an ethylene copolymer.

DOW ENDURANCE™ HFDK-0587 BK offers outstanding extrusion properties and allows high rates, low melt pressure and temperature generation result in outstanding scorch resistance and excellent smoothness under a wide processing window.

Applications

DOW ENDURANCE™ HFDK-0587 BK is recommended as conductor and bonded insulation shielding for medium voltage XLPE power cables.

Specifications

Power cables with conductor and insulation shielding made of DOW ENDURANCE™ HFDK-0587 BK, prepared using sound, commercial fabrication practice, would be expected to meet the following cable specification(s):

- IEC: 60502 and 60840
- HD: 620 S1 and 632 S1
- BS: 6622
- DIN: VDE 0273 and 0263
- EDF: HN-33-S-23 and HN-33-S-52

Consult the regulations for complete details.

Properties¹

Physical	Nominal Value	Unit (English)	Nominal Value	Unit (SI)	Test Method ²
Density	1.10	g/cm ³	1.10	g/cm ³	ISO 1183
Moisture Content	400	ppm	400	ppm	DIN 53715
Mechanical	Nominal Value	Unit (English)	Nominal Value	Unit (SI)	Test Method
Tensile Strength ³	3050	psi	21.0	MPa	IEC 60811-1-1
Tensile Elongation (Break)	200	%	200	%	IEC 60811-1-1
Thermal	Nominal Value	Unit (English)	Nominal Value	Unit (SI)	Test Method
Hot Set ⁴					IEC 811-2-1
Elongation with Load: 392°F (200°C)	40	%	40	%	
Elongation without Load: 392°F (200°C)	0.0	%	0.0	%	

1. Typical properties: these are not to be construed as specifications.
2. ISO: International Standardization Organization
DIN: Deutsche Industrie Norm
IEC: International Electrotechnical Commission
3. 0.98 in/min (25 mm/min)
4. 0.4 MPa

Properties (Cont.)

Aging	Nominal Value	Unit (English)	Nominal Value	Unit (SI)	Test Method
Retention of Tensile Elongation – 10 days 302°F (150°C)	90	%	90	%	IEC 60811-1-1
Retention of Tensile Strength – 10 days 302°F (150°C)	90	%	90	%	IEC 60811-1-1
Electrical	Nominal Value	Unit (English)	Nominal Value	Unit (SI)	Test Method
Volume Resistivity					IEC 60093
73°F (23°C)	10	ohms•cm	10	ohms•cm	
194°F (90°C)	30	ohms•cm	30	ohms•cm	

Additional Information

Smoothness: DOW ENDURANCE™ HFDK-0587 BK meets the strict standards of smoothness established for a crosslinkable semi conductive shielding compound for power cable. Throughout the production process, the product is tested to ensure smoothness. Extruded tapes are scanned by an automatic inspection system in a clean room. The tape smoothness data is managed using an acceptance sampling plan, which ensures that material in each shipping container meets or exceeds the products smoothness standard. For DOW ENDURANCE™ HFDK-0587 BK the material smoothness standard has been designed to meet the stringent CENELEC industry specifications for semi-conductive shielding materials on cable, also during high-speed cable production

Extrusion	Nominal Value	Unit (English)	Nominal Value	Unit (SI)	Test Method
Drying Temperature	158	°F	70	°C	
Drying Time	4.0	hr	4.0	hr	
Melt Temperature	248 to 284	°F	120 to 140	°C	

Extrusion Notes

DOW ENDURANCE™ HFDK-0587 BK provides excellent surface finish and outstanding processing behavior over a broad range of conditions. For optimum results, melt extrusion temperatures in the range of 120 to 140°C are recommended. The following extruder barrel and die setting are recommended as a starting point while learning to process DOW ENDURANCE™ HFDK-0587 BK. Specific machine settings will depend on the extruder and die designs and must be established through conventional practices. In general, a 20/80 mesh screen pack is advised.

- For Maillefer extruders, a dual flight metering screw of 20-22/1, L/D and 2.0-2.5 compression ratio, running at 5–20 rpm is recommended.
- For Troester extruders, if screw cooling is not used, or is used at relatively high settings of around 105°C, Z1 and Z2 should be run somewhat cooler than indicated below.

Recommended drying conditions are 70°C for 4 h.

Default temperature settings for Maillefer 20 D Extruders with normal screw:

- Feed Section: 25°C
- Zone 1: NXW 80°C, MPW 60°C
- Zone 2: 100°C
- Zone 3: 110°C
- Zone 4: 110°C
- Zone 5-6 Clamp: 110°C
- Zone 7-8 Connection: 120°C
- Head/Die: 120°C
- Screw Cooling: None
- Hopper Cooling: None

Properties (Cont.)

Extrusion Notes

Default temperature settings for Troester extruders:

- Feed Section: 50 to 60°C
 - Zone 1: 110 to 115°C
 - Zone 2: 115°C
 - Zone 3: 115°C
 - Zone 4: 115°C
 - Zone 5-6 Clamp: 115 to 120°C
 - Zone 7-8 Connection: 120°C
 - Head/Die: 120°C
 - Screw Cooling: 85 to 105°C
 - Hopper Cooling: None
-

Product Stewardship

The Dow Chemical Company and its subsidiaries ("Dow") has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our Product Stewardship program rests with each and every individual involved with Dow products — from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

Medical Applications Policy

Text goes here NOTICE REGARDING MEDICAL APPLICATION RESTRICTIONS: Dow will not knowingly sell or sample any product or service ("Product") into any commercial or developmental application that is intended for:

- a) long-term or permanent contact with internal bodily fluids or tissues. "Long-term" is contact which exceeds 29 calendar days;
- b) use in cardiac prosthetic devices regardless of the length of time involved ("cardiac prosthetic devices" include, but are not limited to, pacemaker leads and devices, artificial hearts, heart valves, intra-aortic balloons and control systems, and ventricular bypass-assisted devices);
- c) use as a critical component in medical devices that support or sustain human life;
- d) use specifically by pregnant women or in applications designed specifically to promote or interfere with human reproduction; or
- e) use as an ingredient of a pharmaceutical injectable application.

Dow requests that customers considering use of Dow products in medical applications notify Dow so that appropriate assessments may be conducted. Dow does not endorse or claim suitability of its products for specific medical applications. It is the responsibility of the medical device or pharmaceutical manufacturer to determine that the Dow product is safe, lawful, and technically suitable for the intended use. **DOW MAKES NO WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF ANY DOW PRODUCT FOR USE IN MEDICAL APPLICATIONS.**

Contact:
www.dow.com/contact

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the Customer is responsible for determining whether products and the information in this document are appropriate for the Customer's use and for ensuring that the Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Dow assumes no obligation or liability for the information in this document. **NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**

NOTICE: If products are described as "experimental" or "developmental": (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; (3) there is greater potential for Dow to change specifications and/or discontinue production; and (4) although Dow may from time to time provide samples of such products, Dow is not obligated to supply or otherwise commercialize such products for any use or application whatsoever.

NOTICE: This data is based on information Dow believes to be reliable, as demonstrated in controlled laboratory testing. They are offered in good faith, but without guarantee, as conditions and method of use of Dow products are beyond Dow's control. Dow recommends that the prospective user determine the suitability of these materials and suggestions before adopting them on a commercial scale.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability for the accuracy and completeness of such information.

This document is intended for use within Europe, Middle East and Africa.

