



# Dow ENDURANCE™ HFDA-0801 BK

## Supersmooth, Extra-Clean, Crosslinkable Semiconductive Shielding Compound

### Overview

DOW ENDURANCE™ HFDA-0801 BK is a specially formulated semiconductive, vulcanizable compound designed for conductor shield and bonded insulation shield applications in medium and high voltage crosslinked polyethylene insulated cables.(1) DOW ENDURANCE™ HFDA-0801 BK has demonstrated compatibility with copper and aluminum conductors.

DOW ENDURANCE™ HFDA-0801 BK was specifically developed utilizing a special acetylene carbon black to provide a supersmooth surface to achieve best in class performance and yielding a more perfect interface between the extruded shield and the insulation. As a result, significantly improved cable performance can be expected.

### Specifications

DOW ENDURANCE™ HFDA-0801 BK is designed for use in power distribution cables. Cables with conductor and insulation shielding of DOW ENDURANCE™ HFDA-0801 BK, prepared using sound commercial fabrication practice, would be expected to meet the following specifications:

- AEIC: CS8, CS9
- IEC: 60502, 60840, 62067
- ICEA: S-108-720; S-94-649; S-97-682, S-93-639
- DIN: VDE 0276-632, 0276-620
- BS: 6622
- CENELEC: HD620 S1, HD632 S1
- ISO 1872-E/BA, KHXY, 23-G200, C40
- NF: C33-223, C33-226
- UTE: C 33-223

(1) DOW ENDURANCE™ HFDA-0801 BK is recommended for use in conjunction with DOW cross-linked polyethylene and tree-retardant cross-linked polyethylene compounds. For other polymer insulation such as EPR and EPDM's, the user is cautioned to establish the utility of DOW ENDURANCE™ HFDA-0801 BK with each formulation.

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.14 g/cm <sup>3</sup>	1.14 g/cm <sup>3</sup>	ASTM D792
Environmental Stress-Cracking Resistance (ESCR)			ASTM D1693
100% Igepal, F0	> 504 hr	> 504 hr	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength	2100 psi	14.5 MPa	ASTM D638
Tensile Elongation (Break)	200 %	200 %	ASTM D638
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness (Shore D)	53	53	ASTM D2240
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Brittleness Temperature	-40.0 °F	-40.0 °C	ASTM D746
Aging	Nominal Value (English)	Nominal Value (SI)	Test Method
Retention of Tensile Elongation - 1 week			ASTM D638
302°F (150°C)	90 %	90 %	
Retention of Tensile Strength - 1 week			ASTM D638
302°F (150°C)	98 %	98 %	
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Volume Resistivity			ASTM D991
73°F (23°C)	15 ohms-cm	15 ohms-cm	
194°F (90°C)	60 ohms-cm	60 ohms-cm	
266°F (130°C)	65 ohms-cm	65 ohms-cm	

---

**Additional Information**

---

Nominal property values above represent tests on molded stress-relieved slabs. Cure times were 15 minutes at 175°C.

**Extra-Clean Requirements**

- Among many desirable characteristics, DOW ENDURANCE™ HFDA-0801 BK is extra-clean. DOW ENDURANCE™ HFDA-0801 BK typically has less than 0.005% sulfur and less than 0.01% ash. The raw materials used for DOW ENDURANCE™ HFDA-0801 BK are cleaner by design than those used for conventional semiconductive materials. Additional precautions are employed during the manufacture of DOW ENDURANCE™ HFDA-0801 BK relative to conventional conductor shields to prevent introduction of any contamination to the raw materials and to the final product. These low levels of contamination can be expected to play a positive role in the manufacture of a totally extra-clean cable.

**Supersmooth Extruded Surface**

- DOW ENDURANCE™ HFDA-0801 BK meets strict standards of smoothness established for a crosslinkable semiconductive shield compound. The extruded surface of DOW ENDURANCE™ HFDA-0801 BK must meet a smoothness specification that is more rigorous than conventional semiconductive shields. Throughout the production process, the product is tested to ensure smoothness. Extruded tapes are scanned by an automatic inspection system in a clean room. The tape smoothness data is managed using an acceptance sampling plan, which ensures that the shipping container meets or exceeds the product's smoothness standard. The DOW ENDURANCE™ HFDA-0801 BK smoothness standard has been designed to meet the global industry specifications for semiconductive shield materials on medium and high voltage cables.

Each batch of DOW ENDURANCE™ HFDA-0801 BK meets the following smoothness requirement:

- Protrusion Height / Maximum Allowable
  - 60-74 µm / 0 per m<sup>2</sup>
  - >75 µm / 0 per m<sup>2</sup>

**Storage**

- The environment or conditions of storage greatly influences the recommended storage time. Storage should be in accordance with good manufacturing practices. If proper warehousing and storage temperatures [dry conditions, between 50°F and 86°F (10°C and 30°C) in temperature] are utilized, this product may be stored by the customer for up to one year. It is recommended that the practice of using the product on a first-in / first-out basis be established. Storage under extreme conditions may affect the quality, processing, or performance of the product.

---

<b>Extrusion</b>	<b>Nominal Value (English)</b>	<b>Nominal Value (SI)</b>
Drying Temperature	140 to 158 °F	60 to 70 °C
Drying Time	< 6.0 hr	< 6.0 hr
Melt Temperature	250 to 284 °F	121 to 140 °C

---

**Extrusion Notes**

DOW ENDURANCE™ HFDA-0801 BK provides excellent surface finish and outstanding output rates over a broad range of conditions. For optimum results, use melt extrusion temperatures in the suggested range of 250 to 285°F (121 to 140°C) to avoid pre-cure or scorch. Extruder barrel settings of 110°C (230°F) are suggested as a starting point while learning to process DOW ENDURANCE™ HFDA-0801 BK. Specific machine settings will depend on the extruder design and must be established through conventional practices.

Dehumidified air hopper drying at 140-160°F (60-70°C) for up to six hours may be employed to remove residual moisture prior to extrusion. Drying is not necessary for DOW ENDURANCE™ HFDA-0801 BK due to the lower moisture absorption characteristics relative to conventional semiconductive products.

**Notes**

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

## Product Stewardship

The Dow Chemical Company and its subsidiaries ("Dow") has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our Product Stewardship program rests with each and every individual involved with Dow products — from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

## Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

## Medical Applications Policy

NOTICE REGARDING MEDICAL APPLICATION RESTRICTIONS: Dow will not knowingly sell or sample any product or service ("Product") into any commercial or developmental application that is intended for:

- long-term or permanent contact with internal bodily fluids or tissues. "Long-term" is contact which exceeds 72 continuous hours;
- use in cardiac prosthetic devices regardless of the length of time involved ("cardiac prosthetic devices" include, but are not limited to, pacemaker leads and devices, artificial hearts, heart valves, intra-aortic balloons and control systems, and ventricular bypass-assisted devices);
- use as a critical component in medical devices that support or sustain human life; or
- use specifically by pregnant women or in applications designed specifically to promote or interfere with human reproduction.

Dow requests that customers considering use of Dow products in medical applications notify Dow so that appropriate assessments may be conducted. Dow does not endorse or claim suitability of its products for specific medical applications. It is the responsibility of the medical device or pharmaceutical manufacturer to determine that the Dow product is safe, lawful, and technically suitable for the intended use. **DOW MAKES NO WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF ANY DOW PRODUCT FOR USE IN MEDICAL APPLICATIONS.**

## Disclaimer

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the Customer is responsible for determining whether products and the information in this document are appropriate for the Customer's use and for ensuring that the Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Dow assumes no obligation or liability for the information in this document. **NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**

NOTICE: If products are described as "experimental" or "developmental": (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; (3) there is greater potential for Dow to change specifications and/or discontinue production; and (4) although Dow may from time to time provide samples of such products, Dow is not obligated to supply or otherwise commercialize such products for any use or application whatsoever.

NOTICE: This data is based on information Dow believes to be reliable, as demonstrated in controlled laboratory testing. They are offered in good faith, but without guarantee, as conditions and method of use of Dow products are beyond Dow's control. Dow recommends that the prospective user determine the suitability of these materials and suggestions before adopting them on a commercial scale.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability for the accuracy and completeness of such information.

## Additional Information

<b>North America</b>		<b>Europe/Middle East</b>	+800-3694-6367
U.S. & Canada:	1-800-441-4369		+31-11567-2626
	1-989-832-1426	Italy:	+800-783-825
Mexico:	+1-800-441-4369		
<b>Latin America</b>		<b>South Africa</b>	+800-99-5078
Argentina:	+54-11-4319-0100		
Brazil:	+55-11-5188-9000		
Colombia:	+57-1-219-6000	<b>Asia Pacific</b>	+800-7776-7776
Mexico:	+52-55-5201-4700		+603-7965-5392

[www.dowplastics.com](http://www.dowplastics.com)

This document is intended for use within Africa & Middle East, Asia Pacific, Europe, Latin America, North America

Published: 2013-02-20

© 2019 The Dow Chemical Company

