



## Technical Data Sheet

### SILASTIC™ DY 37-071 U Fluorosilicone Rubber

70 Durometer, general molding use, uncatalyzed fluorosilicone rubber

#### Features & Benefits

- 70 JIS-Type A hardness
- Excellent fluid resistance to most hydrocarbon and silicone fluids
- Serviceable over wide temperature range
- Pigmentable
- Good tensile strength
- Low compression set

#### Composition

- Fluorosilicone rubber (FSR)
- Uncatalyzed stock (U-stock)

#### Applications

- Engine seal and gaskets
- Fuel system connector seals
- Flexible diaphragms and valves
- Turbocharger hose liners
- Rubber parts for which oil and fuel resistance is required

#### Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

Test <sup>1</sup>	Property	Unit	Result
<b>As supplied</b>			
	Appearance		Light yellow
JIS K 6249	Plasticity	mm/100	324
<b>As cured</b>			
JIS K 6249	Density	g/cm <sup>3</sup>	1.45
JIS K 6249	Durometer hardness, JIS Type A		70
JIS K 6249	Tensile strength, JIS#3	MPa	9.2
JIS K 6249	Elongation, JIS#3	%	220
JIS K 6249	Modulus at 100% elongation, JIS#3	MPa	3.7

1. JIS: Japanese Industrial Standard.

Properties obtained using 1.0 part of SILASTIC™ RC-4 50P FD Rubber Additive (2,5-bis(tert-butylperoxy)-2,5-dimethyl hexane, 50% masterbatch) per 100 parts of SILASTIC™ DY 37-071 U Fluorosilicone Rubber: molded 10 minutes at 170°C (338°F) and post-cured 4 hours at 200°C (392°F).

## Typical Properties (Cont.)

Test	Property	Unit	Result
JIS K 6249	Tear strength, crescent	N/mm	11
JIS K 6249	Tear strength, angle	N/mm	25
JIS K 6249	Linear shrinkage, disc <sup>2</sup>	%	3.4
JIS K 6255	Rebound, Lupke	%	33
JIS K 6249	Compression set, (70 hours at 150°C/302°F)	%	6
JIS K 6249	Change rate in volume (Fuel C, 72 hours at 23°C/73°F)	%	23

2. Linear shrinkage depends on the curing conditions such as type of curing agent, curing temperature and size of molded product.

## How to Use

### Milling

For adding vulcanizing agents, additives, and / or pigments or blending, milling with a two-roll mill is the most suitable process. Milling time should be carefully decided to secure uniformity of materials.

### Vulcanization

SILASTIC™ DY 37-071 U Fluorosilicone Rubber requires the addition of a vulcanizing agent. SILASTIC™ RC-4 50P FD Rubber Additive is recommended for molding. Standard cure temperature is 170°C (338°F), and its cure time depends on the thickness of final products. Post-cure condition would be 4 hours at 200°C (392°F) after molding in most cases.

### Compounding

SILASTIC™ DY 37-071 U Fluorosilicone Rubber can be blended with other fluorosilicone rubbers to modify the durometer of the compound. The physical properties of this product can be modified using a range of SILASTIC™ or XIAMETER™ additives. Further, SILASTIC™ DY 37-071 U Fluorosilicone Rubber can be pigmented to almost any color shade desired.

## Handling Precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

## Usable Life and Storage

Product should be stored at or below 32°C(90°F) in original, unopened containers, this product has usable life of 270 days from the date of production.

## Packaging Information

SILASTIC™ DY 37-071 U Fluorosilicone Rubber is available in 20 kg (44 lb) boxes.

## Limitations

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

## Health and Environmental Information

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, [dow.com](http://dow.com) or consult your local Dow representative.

## Disposal Considerations

Dispose in accordance with all local, state (provincial) and federal regulations. Empty containers may contain hazardous residues. This material and its container must be disposed in a safe and legal manner.

It is the user's responsibility to verify that treatment and disposal procedures comply with local, state (provincial) and federal regulations. Contact your Dow Technical Representative for more information.

## Product Stewardship

Dow has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Dow products - from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

## Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

**Table 1:**

Heat and Fluid Resistance of SILASTIC™ DY 37-071 U Fluorosilicone Rubber

Test	Unit	Result
<b>Heat Aged, 70 Hours at 200°C (392°F)</b>		
Hardness Change	Points	-1
Tensile Change	%	-18
Elongation Change	%	-12
<b>IRM 903 Oil, 70 Hours at 150°C (302°F)</b>		
Hardness Change	Points	-4
Tensile Change	%	-11
Elongation Change	%	-13
Volume Change	%	+4

dow.com

**NOTICE:** No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

