



## Technical Data Sheet

### SILASTIC™ SE 6770 U-P Silicone Rubber

75 Durometer, molding, electrically conductivity, uncatalyzed silicone rubber

#### Features & Benefits

- 75 JIS-Type A hardness
- High electrically conductivity
- Serviceable over wide temperature range

#### Composition

- Silicone rubber (HCR)
- Uncatalyzed stock (U-stock)

#### Applications

- Molding
- Rubber contacts
- Transfer rollers
- Pigment

#### Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

Test	Property	Unit	Result
<b>As supplied</b>			
	Appearance		Black
JIS K 6249	Plasticity	mm/100	670
<b>As cured</b>			
JIS K 6249	Density	g/cm <sup>3</sup>	1.21
JIS K 6249	Durometer hardness, JIS type A		76
JIS K 6249	Tensile strength, JIS#3	MPa	7.3
JIS K 6249	Elongation, JIS#3	%	120
JIS K 6249	Modulus at 100% elongation, JIS#3	MPa	6.44
JIS K 6249	Tear strength, crescent	N/mm	8
JIS K 6249	Tear strength, angle	N/mm	10

1. JIS: Japanese Industrial Standard.

Properties obtained using 2.0 part of SILASTIC™ RC-4 50P FD Rubber Additive (2,5-bis(tert-butylperoxy)-2,5-dimethyl hexane, 50% masterbatch) per 100 parts of SILASTIC™ SE 6770 U-P Silicone Rubber: molded 10 minutes at 170°C(338°F) and post-cured 4 hours at 200°C (392°F).

## Typical Properties (Cont.)

Test	Property	Unit	Result
JIS K 6249	Linear shrinkage, disc <sup>2</sup>	%	3.9
JIS K 6255	Rebound, Lupke	%	52
JIS K 6249	Compression set, 180°C /22h	%	33
JIS K 6249	Volume resistance	Ω·m	1.9

2. Linear shrinkage depends on the curing conditions such as type of curing agent, curing temperature and size of molded product.

## How to Use

### Milling

For adding vulcanizing agents and / or additives or blending, milling with a two-roll mill is the most suitable process. Milling time should be carefully decided to secure uniformity of materials.

### Vulcanization

SILASTIC™ SE 6770 U-P Silicone Rubber requires the addition of a vulcanizing agent. SILASTIC™ RC-4 50P FD Rubber Additive is recommended for molding. Standard cure temperature is 170°C (338°F), and its cure time depends on the thickness of final products. Post-cure condition would be 4 hours at 200°C (392°F) after molding in most cases. The other SILASTIC™ curing agents are also available for vulcanization.

### Compounding

SILASTIC™ SE 6770 U-P Silicone Rubber can be blended with other bases to modify the durometer of the compound. The physical properties of this product can be modified using a range of SILASTIC™ or XIAMETER™ additives.

## Handling Precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

## Usable Life and Storage

Product should be stored at or below 32°C(90°F) in original, unopened containers, this product has usable life of 720 days from the date of production.

## Packaging Information

SILASTIC™ SE 6770 U-P Silicone Rubber is available in 20 kg (44 lb) boxes.

## Limitations

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

## Health and Environmental Information

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, [dow.com](http://dow.com) or consult your local Dow representative.

## Disposal Considerations

Dispose in accordance with all local, state (provincial) and federal regulations. Empty containers may contain hazardous residues. This material and its container must be disposed in a safe and legal manner.

It is the user's responsibility to verify that treatment and disposal procedures comply with local, state (provincial) and federal regulations. Contact your Dow Technical Representative for more information.

## Product Stewardship

Dow has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Dow products - from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

## Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

**Table 1:** Heat Resistance of SILASTIC™ SE 6770 U-P Silicone Rubber

Test	Unit	Result
<b>Heat Aged, 72 Hours at 200°C (392°F)</b>		
Hardness Change	points	+2
Tensile Change	%	+4
Elongation Change	%	+2
<b>Heat Aged, 72 Hours at 250°C (482°F)</b>		
Hardness Change	points	0
Tensile Change	%	-12
Elongation Change	%	-3

Properties obtained using 2.0 part of SILASTIC™ RC-4 50P FD Rubber Additive (2,5-bis(tert-butylperoxy)-2,5-dimethyl hexane, 50% masterbatch) per 100 parts of SILASTIC™ SE 6770 U-P Silicone Rubber: molded 10 minutes at 170°C(338°F) and post-cured 4 hours at 200°C (392°F).

dow.com

**NOTICE:** No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

