

DOW SILICONES CORP 2200 W Salzburg Rd Midland, MI 48686 United States



## Xiameter RBL-9590-30 LSR

Silicone "Room Temperature Vulcanizing" (RTV), two liquid components, two component, addition-cure, vinyl platinum catalyzed silicone

Flammability	Value	Test Method
Flame Rating (3.0 mm, NC)	V-1	UL 94 IEC 60695-11-10, -20
Thermal	Value	Test Method
RTI Elec (3.0 mm)	150 °C	UL 746
RTI Str (3.0 mm)	150 °C	UL 746