



APPEEL™ 72D727

Peelable Resin

General Information

Product Description APPEEL™ 72D727 is a blown or cast film resin designed to be a sealing layer to film or sheet lidding applications. It provides a peelable seal to a number of materials including HDPE, LLDPE, LDPE, EVA, and Ionomer.

APPEEL™ 72D727 is a modified ionomer polymer available in pellet form for use in conventional extrusion and coextrusion equipment designed to process polyethylene resins.

Status

Material Status Commercial: Active

Typical Characteristics

Uses Lidding Sealant

Typical Properties

Physical	Nominal Values	Test Method(s)	
*Density ()	0.94 g/cm ³	ASTM D792	ISO 1183
*Melt Flow Index (190°C/2.16kg)	3.5 g/10 min	ASTM D1238	ISO 1133
Thermal	Nominal Values	Test Method(s)	
*Melting Point (DSC)	94 °C (201.2 °F)	ASTM D3418	ISO 3146
Vicat Softening Point ()	68 °C (154.4 °F)	ASTM D1525	ISO 306

Heat Seal Evaluation The performance of any sealant resin should be evaluated within the context of the application. The sealant is designed to bond to particular substrate(s). Many variables can affect seal strength, including the physical properties of the substrate being sealed to, thickness, flange or surface design, heat seal temperature, dwell time and pressure. The condition and type of the sealing equipment used, such as roller sealers versus platen seal mechanisms can make a significant difference.

In most cases sealant peel strength is used as a measure of performance. Although this is a convenient test, peel strength is affected not only by substrate adhesion but also by peel angle, separation rate, ambient temperature, tensile and modulus properties of the materials, and often by the time elapsed since the formation of the bond.

If sealant peel strength is used as a measure of sealant performance, it is imperative that peel strength be evaluated not only at the time of initial heat sealing the lid to the substrate, but throughout the life of the product and under all the conditions to which the sealant will be exposed. Only then does peel strength provide a reliable indication of adhesive performance in the specific application.

Processing Information

*Maximum Processing Temperature 235 °C (455 °F)

General Processing Information If the process is stopped for short periods of time, the screw for the APPEEL™ extruder should be kept turning at a low rpm to keep material flowing.

After processing APPEEL™, purge the material out using a polyethylene resin, preferably with a lower melt flow rate than the APPEEL™ resin in use. The "Disco Purge Method" is suggested as the preferred purging method, as this method usually results in a more effective purging process. Information on the Disco Purge Method can be obtained via your Dow Sales Representative.

Never shut down the extrusion system with APPEEL™ in the extruder and die. Properly purge out the APPEEL™ with a polyethylene, and shut down the line with polyethylene or polypropylene in the system.

Materials of construction used in the processing of this resin should be corrosion resistant. Stainless steels of the types 316, 15-5PH, and 17-4PH are excellent, as is quality chrome or nickel plating, and in particular duplex chrome plating. Type 410 stainless steel is satisfactory, but needs to be tempered at a minimum temperature of 600°C (1112°F) to avoid hydrogen-assisted stress corrosion cracking. Alloy steels such as 4140 are borderline in performance. Carbon steels are not satisfactory. While stainless steels can provide adequate corrosion protection, in some cases severe purging difficulties have been encountered. Nickel plating has been satisfactory, but experiments have shown that chrome surfaces have the least adhesion to acid containing polymers. In recent years, the quality of chrome plating has been deteriorating due to environmental pressures, and the corrosion protection has not always been adequate. Chrome over top of stainless steel seems to provide the best combination for corrosion protection and ease of purging.

Blown Film

Nominal Values

Processing Information

Blown Film: In blown film coextrusion processes the temperature of the APPEEL™ 72D727 should be maintained in the 160 - 185° C range. .

Following is an example of a suggested temperature profile for blown film processing. Adjustments would then be made to suit the individual process and applications needs.

Feed Zone	140 °C (284 °F)
Second Zone	150 °C (302 °F)
Third Zone	160 °C (320 °F)
Fourth Zone	180 °C (356 °F)
Fifth Zone	180 °C (356 °F)
Adapter Zone	180 °C (356 °F)
Die Zone	170 °C (338 °F)

FDA Status Information

APPEEL™ 72D727 resin complies with Food and Drug Administration Regulation 21 CFR 177.1330, subject to the limitations and requirements therein. This Regulation describes polymers that may be used in contact with food, subject to the finished food-contact article meeting the extractive limitations under the intended conditions of use, as shown in paragraph (c) of the Regulation.

The information and certifications provided herein are based on data we believe to be reliable, to the best of our knowledge. The information and certifications apply only to the specific material designated herein as sold by Dow and do not apply to use in any process or in combination with any other material. They are provided at the request of and without charge to our customers. Accordingly, Dow cannot guarantee or warrant such certifications or information and assumes no liability for their use.

Regulatory Information

In Europe a diversity of regulations apply in various countries. In addition, constant changes linked to the effort of their harmonization under the umbrella of European Union Directive can be observed. This makes it impossible to accurately describe the food contact status in this brochure. Updated statements describing the situation in the various European countries can be obtained through your local sales representative.

Safety & Handling

For information on appropriate Handling & Storage of this polymeric resin, please refer to the material Safety Data Sheet.

A Product Safety Bulletin, material Safety Data Sheet, and/or more detailed information on extrusion processing and/or compounding of this polymeric resin for specific applications are available from your Dow representative.

Product Stewardship

Dow has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Dow products - from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

Medical Applications Policy

Any and all medical application use of Dow materials, whether a device, a component, or any type of primary or secondary packaging of a medically related object or substance, needs to be reviewed and approved by Dow before any Dow material can be tested in such application.

Dow requests that customers considering use of Dow products in medical applications notify Dow so that appropriate assessments may be conducted. Dow does not endorse or claim suitability of its products for specific medical applications. It is the responsibility of the medical device or pharmaceutical manufacturer to determine that the Dow product is safe, lawful, and technically suitable for the intended use. **DOW MAKES NO WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF ANY DOW PRODUCT FOR USE IN MEDICAL APPLICATIONS.**

For further information contact your Dow sales or technical representative to request a Medical Application Review Request Form. Additional details of Dow's Medical Applications Policy are available at:

<https://www.dow.com/en-us/support/product-safety.html>

Tobacco and Marijuana Policy

Dow does not support or intend for its products to be used, directly or indirectly, in the production of tobacco, the manufacture of tobacco products, the manufacture and use of electronic cigarettes (including vaping devices), the production of marijuana, or the manufacture of marijuana products intended for human consumption, where the Dow product (or its residues) may be present in the finished product or be alleged to facilitate the delivery of nicotine, other tobacco components, marijuana, or marijuana components.

Harmful Applications Policy

Dow does not intend for its products to be used in applications specifically intended to harm humans.

Disclaimer

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the Customer is responsible for determining whether products and the information in this document are appropriate for the Customer's use and for ensuring that the Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Dow assumes no obligation or liability for the information in this document. **NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**

NOTICE: If products are described as "experimental" or "developmental": (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; (3) there is greater potential for Dow to change specifications and/or discontinue production; and (4) although Dow may from time to time provide samples of such products, Dow is not obligated to supply or otherwise commercialize such products for any use or application whatsoever.

For additional information, not covered by the content of this document, contact us via our web site

http://www.dow.com/products_services

Revision Date: 26-February-2021

P&SP Disclaimer

Additional Information

To contact Dow via Toll-Free or Local Toll phone numbers in specific countries, please see the following webpage:

<https://www.dow.com/en-us/support/contact-representative.html>

<http://www.dow.com>

Updated February 2021

© 2019 The Dow Chemical Company

Version: 118.0

Last modified at 7/29/2019 1:41 PM

Form No. 914-024-01-0221 DOW