



## Dow Packaging & Specialty Plastics

### Product Data Sheet

#### DOW™ LDPE 6611

#### Purge Resin

##### General Information

**Product Description** DOW™ LDPE 6611 is a high viscosity low density polyethylene resin that contains various additives to assist in purging and cleaning the extruder. This polymer is formulated with agents to help it wet and scour metal surfaces within the extrusion system. It also contains a blowing agent which helps to disrupt normal flow patterns and enhance scouring action. The resin normally will foam, snap, and crackle as it leaves the die. Odors that are associated with ammonia and fish are detectable from the extrudate and feed hopper. When extruded, the resin has a grayish brown color and a very high viscosity at the die exit.

##### Status

**Material Status** Commercial: Active

**Other Restrictions** **Precautions:**  
\*\*\* Adequate ventilation is required for use. Fumes from extrusion can be irritating to the eyes, nose, and throat. Fumes from high temperature extrusion of polyolefin resins contain various products of decomposition that may be toxic.  
\*\*\* Exploding bubbles can spit hot polymer as the melt exits the die. Proper protective apparel, including eye protection, should be worn.  
DOW™ LDPE 6611 should not be extruded or exposed to temperatures above 310°C (590°F).  
  
DOW™ LDPE 6611 does not comply with FDA regulations, so complete purging from the extrusion system is required after use.  
DOW™ LDPE 6611 contains silicon dioxide to assist in scouring hard deposits from metal surfaces. Excessive use of this purge compound can cause premature equipment wear, particularly in some extrusion systems that are soft nickel plated.

##### Typical Characteristics

**Applications** DOW™ LDPE 6611 is not required for normal transitions into and out of SURLYN™ ionomer resins, NUCREL™ acid copolymer resins, and other common polyolefins. The "Disco Purge / Transition Procedure" is recommended for use during these normal transitions, and special purging compounds such as DOW™ LDPE 6611 are not part of this procedure. There are instances, however, when it is practical to use a special purging compound like DOW™ LDPE 6611. For a copy of the "Disco Purge / Transition Procedure", please contact your Dow Packaging & Industrial Polymer representative.

##### Examples for use include:

- Cleaning particularly dirty extruders.
  - Removing die lines caused by oxidized polymer deposits.
  - Purging extruders that have chronic purging problems (gels) following runs of SURLYN™ resins, NUCREL™ resins, ELVAX™ ethylene vinyl acetate resins, or other specialty resins. Consulting your technical representative is also highly recommended for these cases.
  - Purging prior to extrusion jobs that are particularly sensitive to gels.
  - Facilitating purging for shutdowns when normal Disco Purging has not proven effective. A shutdown is any period of time when the extruder will be completely turned off, such as a weekend or maintenance outage. It is very important that specialty copolymers such as SURLYN™ and NUCREL™ be completely purged before such a shutdown, as the cool-down, heat-up, and soak periods allow plenty of time to cause significant gel problems.
  - Facilitating rapid removal of pigments from the extruder.
  - DOW™ LDPE 6611 has also been used to facilitate pulling and cleaning large diameter extrusion screws. However, acrylic purge material is normally used for this purpose.
  - The high viscosity of DOW™ LDPE 6611 lends itself to easy cleaning of hardware during disassembly, because it peels rather than smearing along the metal surfaces.
- Although most frequently used on flat die extrusion equipment, DOW™ LDPE 6611



can also be used for round die converting equipment as well. It can be difficult to purge DOW™ LDPE 6611 out of standard spiral-fed blown film dies, unless a very low melt index polyethylene is available for this purpose (0.5 MI LDPE or 1.0 MI LLDPE).

Typical Properties			
Physical	Nominal Values	Test Method(s)	
*Density ( )	0.97 g/cm <sup>3</sup>	ASTM D792	ISO 1183
*Melt Flow Index ( 190°C/2.16kg )	approx. 0.4 g/10 min	ASTM D1238	ISO 1133
Thermal	Nominal Values	Test Method(s)	
*Melting Point ( DSC )	109 °C ( 228.2 °F )	ASTM D3418	ISO 3146
Freezing Point ( DSC )	95 °C ( 203 °F )	ASTM D3418	ISO 3146
Processing Information			
*Maximum Processing Temperature	285 °C ( 545 °F )		
General Processing Information	<p>*** DOW™ LDPE 6611 has a very specific procedure for proper useage. Please consult with your local Dow technical representative to request a copy of the procedure.</p> <p>*** This procedure specifies how to properly utilize the resin, and in what proper quantities for a given size extrusion system. Improper useage of the material will lessen its effectiveness, and possibly make it more challenging to remove from the system using a polyethylene resin with the appropriate melt flow rate.</p> <p>To activate the blowing agent, the resin must be extruded above about 221°C (430°F). Purging efficiency may be somewhat reduced if the resin does not foam.</p> <p>The maximum recommended temperature for use in purging extrusion equipment is 285C (545F). This is due to the volatility of the blowing agent, and the increased spitting of polymer from the die exit as a hazard. The highest temperature to use in any environment where operators are not exposed to the polymer exiting the die would be a maximum of 310C (590F). However please note that experience has found that the purge compound is effective at 285C (545F), and higher temperatures are not necessary for processing. Thus for operations safety, 285C (545F) as a maximum use temperature is recommended.</p>		
FDA Status Information	DOW™ LDPE 6611 Resin does not comply with FDA regulations permitting contact with food. This product is designed to be used to clean extruders and not for manufacture of food contact materials. After the Dow 6611 has been used as a purge compound, we recommend that its residues be purged from the extruder with a food grade polymer.		
Regulatory Information	For information on regulatory compliance outside of the U.S.A., consult your local Dow representative.		
Safety & Handling	<p>For information on appropriate Handling &amp; Storage of this polymeric resin, please refer to the material Safety Data Sheet.</p> <p>A Product Safety Bulletin, material Safety Data Sheet, and/or more detailed information on extrusion processing and/or compounding of this polymeric resin for specific applications are available from your Dow representative.</p>		



## Product Stewardship

Dow has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Dow products - from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

## Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

## Medical Applications Policy

Any and all medical application use of Dow materials, whether a device, a component, or any type of primary or secondary packaging of a medically related object or substance, needs to be reviewed and approved by Dow before any Dow material can be tested in such application.

Dow requests that customers considering use of Dow products in medical applications notify Dow so that appropriate assessments may be conducted. Dow does not endorse or claim suitability of its products for specific medical applications. It is the responsibility of the medical device or pharmaceutical manufacturer to determine that the Dow product is safe, lawful, and technically suitable for the intended use. **DOW MAKES NO WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF ANY DOW PRODUCT FOR USE IN MEDICAL APPLICATIONS.**

For further information contact your Dow sales or technical representative to request a Medical Application Review Request Form. Additional details of Dow's Medical Applications Policy are available at:

<https://www.dow.com/en-us/support/product-safety.html>

## Tobacco and Marijuana Policy

Dow does not support or intend for its products to be used, directly or indirectly, in the production of tobacco, the manufacture of tobacco products, the manufacture and use of electronic cigarettes (including vaping devices), the production of marijuana, or the manufacture of marijuana products intended for human consumption, where the Dow product (or its residues) may be present in the finished product or be alleged to facilitate the delivery of nicotine, other tobacco components, marijuana, or marijuana components.

## Harmful Applications Policy

Dow does not intend for its products to be used in applications specifically intended to harm humans.

## Disclaimer

**NOTICE:** No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the Customer is responsible for determining whether products and the information in this document are appropriate for the Customer's use and for ensuring that the Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Dow assumes no obligation or liability for the information in this document. **NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**

**NOTICE:** If products are described as "experimental" or "developmental": (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; (3) there is greater potential for Dow to change specifications and/or discontinue production; and (4) although Dow may from time to time provide samples of such products, Dow is not obligated to supply or otherwise commercialize such products for any use or application whatsoever.

For additional information, not covered by the content of this document, contact us via our web site

[http://www.dow.com/products\\_services](http://www.dow.com/products_services)



**Revision Date: 26-February-2021**

**P&SP Disclaimer**

**Additional Information**

To contact Dow via Toll-Free or Local Toll phone numbers in specific countries, please see the following webpage:

<https://www.dow.com/en-us/support/contact-representative.html>

<http://www.dow.com>

**Updated February 2021**

**© 2019 The Dow Chemical Company**

Version: 178.0

Last modified at 12/9/2019 1:57 PM