



Technical Data Sheet

XIAMETER™ RBB-2880-60 Silicone Rubber

A silicone rubber designed for use in a variety of molded goods

Features & Benefits

- Translucency
- Wide service temperature
- Easy to process

Applications

- General molded rubber parts such as keypad, gasket, packing and others

Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

ASTM ¹	Property	Unit	Result ²
	Appearance		Translucent
D792	Specific gravity		1.18
D2240	Hardness	Shore A	61
D412	Tensile strength	MPa	8.5
D412	Elongation	%	400
D624	Tear strength, angle	KN/m	27

1. ASTM: American Society for Testing and Materials
2. Properties obtained using 0.6 part SILASTIC™ RC-4 50P FD Rubber Additive (2,5-bis (tert-butylperoxy)-2,5-dimethyl hexane) on 2 mm thick slabs: molded 10 minutes at 170°C and post-cured 4 hours at 200°C

Description

XIAMETER™ RBB-2880-60 Silicone Rubber is a 60 durometer general purpose silicone rubber compound especially designed to provide good results when making molded parts. It can be blended with other XIAMETER™ silicone rubbers to obtain intermediate hardness. It is translucent and therefore can be easily pigmented to obtain most any color shade desired.

XIAMETER RBB-2880-60 Silicone Rubber is primarily used for molded parts such as keypads, gasket, and other miscellaneous goods.

How To Use

For blending or pigmenting, milling with two-roll mill is the most suitable process. Milling time should be carefully decided to secure uniformity of materials.

UNRESTRICTED – May be shared with anyone

™Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow

XIAMETER™ RBB-2880-60 Silicone Rubber

© 2017 The Dow Chemical Company. All rights reserved.

How To Use (Cont.)	When molding, Dow recommends using 0.6 to 1.0 part of SILASTIC RC-4 50P FD Rubber Additive to 100 parts of the stock. Standard cure temperature is 170°C (338°F), and its cure time depends on the thickness of final products. Post cure condition would be 4 hours at 200°C (392°F) after molding in most cases.
Handling Precautions	PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT WWW.CONSUMER.DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.
Usable Life And Storage	When stored at or below 50°C (122°F) in the original unopened containers, this product has a usable life of 9 months from the date of production.
Limitations	This product is neither tested nor represented as suitable for medical or pharmaceutical uses.
Health And Environmental Information	To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area. For further information, please see our website, www.consumer.dow.com or consult your local Dow representative.

<http://www.xiameter.com>

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DOW SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

DOW DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

