



74 Kent Street
Brooklyn, New York 11222-1517

Phone (718) 383-5080
Fax (718) 383-7445
E-mail: dllabs@aol.com

Accredited by National Voluntary Laboratory Accreditation Program - Lab Code 100252
ISO / IEC 17025 and relevant requirements of ISO 9002

May 29, 2009

Dow Corning Corporation
2200 W. Salzburg Road
DC-4 Sealants Test Lab 3A4
Auburn, MI 48611

Att: **Ms. Kelly Allore**

DL-15761 CR
Via FAX (989) 496-4374

OBJECTIVE

To test a sealant for conformance to the requirements outlined in ASTM C 1184-05, "Standard Specification for Structural Silicone Sealants", Type S, Use G.

PRODUCT TESTED

Dow Corning[®] **995 Silicone Building Sealant, Black**, Lot: 5161754

TEST PROCEDURES

The sealant was tested in accordance with the procedures outlined in Paragraphs 8. Test Methods and 9. Shelf Life.

TEST RESULTS

The test results can be found in the Appendix.

CONCLUSION

The submitted sample of ***Dow Corning***[®] **995 Silicone Building Sealant** conforms to the requirements outlined in ASTM C 1184, Table 1 – Requirements for Physical, Mechanical and Performance Qualities of a Sealant.

DL Labs, Inc.

A handwritten signature in black ink, appearing to read 'Mario Lazaro, Jr.', is written over the printed name.

Mario Lazaro, Jr.
Assistant Technical Director



APPENDIX

TEST RESULTS

**Dow Corning® 995 Silicone Building Sealant, Black
ASTM C 1184 - Table I Requirements for Physical, Mechanical
and Performance Qualities of a Sealant**

<u>Par.</u>	<u>ASTM</u>	<u>Test</u>	<u>Requirement</u>	<u>Result</u>
8.1	C 639	Rheological Properties Vertical 122°F 40°F Horizontal 122°F 40°F	3/16" max. flow No deformation	No flow No flow No deformation No deformation
8.2	C 603	Extrusion Rate	10 seconds max.	1½-seconds
8.3	C 661	Hardness – Shore A-2	Between 20 and 60	42
8.4	C 792	Effect of Heat Aging @ 88°C Weight Loss Cracking Chalking	10% max. None None	0.3% wt. loss No cracking No chalking
8.5	C 679	Tack-Free Time	3 hours max.	80-minutes
8.6	C 1135	Tensile Adhesion Standard Conditions 88° C (190° F) -29° C (-20° F) Water Immersion 5,000 hrs. Weathering	50 psi min.	180 psi 125 psi 200 psi 170 psi 235 psi
9.1		Shelf Life	6-months min.	6-months