



**Polyglycol P-1200**  
Polypropylene Glycol

**Product Description**

CAS # 25322-69-4  
CTFA NOMENCLATURE — PPG-20

Polyglycol P-1200 is a linear polymer produced by controlled, catalysed reaction between propylene oxide and water. The letter P and the number 1200 indicate that the polymer is propylene oxide based and that the approximate average molecular weight is 1200.

PPG P-1200, as this product is also known, is a clear, viscous liquid at room temperature. It has a low pour point and, unlike the higher molecular weight PPGs, is completely soluble in water at 77°F (25°C). It loses its water solubility at higher temperatures.

Like all polypropylene glycols, Polyglycol P1200 is soluble in all proportions with any organic solids and liquids, the main exception being long chain aliphatic hydrocarbons.

Polyglycol P1200 possesses excellent lubricity and has a low vapor pressure. Under extreme heating conditions it does not form coke nor does it form a varnish. Decomposition products are low boiling products that are either lost as volatiles or soluble in the polypropylene glycol.

**Typical Physical Properties**

<u>Property (Unit)</u>	<u>Typical Value</u>	<u>Test Method</u>
Flash point	>302°F (>150°C)	ASTM D 92 (COC)
Viscosity @ 77°F (25°C) (cSt)	160	ASTM D 445 / D 446
Viscosity @ 212°F (100°C) (cSt)	13	ASTM D 445 / D 446
Specific Gravity (g/cm <sup>3</sup> @ 77°F(25°C)/ 77°F (25°C))	1.003	ASTM D 892
Pour point	-42°F (-41°C)	ASTM D 97

Notice: The information and data contained herein do not constitute sales specifications. No liability, warranty or guarantee of final product performance is created by this document.

**Applications**

As PPG P-1200 is water-soluble, it is used in areas not usually associated with the higher molecular weight PPGs. For example it is used as a dust adhesive fluid, as solvent/coupler for inks and pesticide formulations. PPG P-1200 is also used to make resins, fatty acid esters, lubricants, metal working fluids and as plasticizer.

## Safe Use and Handling

Dow polypropylene glycols are relatively easy to store and handle. They can be stored in bulk in steel tanks, which should be padded with nitrogen or any other inert gas to prevent air from entering the tank. If slight iron pickup and color changes cannot be tolerated then the storage tanks should be constructed from stainless steel.

To ease the handling of polypropylene glycols somewhat, higher storage temperatures should be considered to keep the viscosity of the polyglycols within limits suitable for the pumping equipment available. The maximum storage temperature should not exceed 104°F (40°C) to avoid the risk of product degradation. Pipelines may also require insulation and/or tracing to maintain suitable product temperatures.

Although PPGs have very low pour points, especially polyglycols P2000 and P4000 become very viscous at low temperatures. Consequently, it is recommended that they be stored in tanks which are well insulated and heated. Externally located heating devices are preferable to internally sited ones. With external heating the risk of accelerating product deterioration is greatly reduced.

Similarly drums should be stored under cover or preferably inside a warehouse, to maintain the temperature of the polyglycol at a level which allows for easy discharge.

The shelf life of properly stored bulk and unopened drums is, at least, 24 months.

## Product Stewardship

Dow encourages its customers and potential users to review their applications from the standpoint of human health and environmental aspects. To help ensure that Dow products are not used in ways for which they are not intended or tested, Dow personnel will assist customers in dealing with environmental and product safety considerations. Dow literature, including Material Safety Data Sheets, should be consulted prior to use.

### Contact information:

North America: 1-800-447-4369  
Fax: 1-989-832-1465  
Europe: +800-3-694-6367  
Tel: +32-3-450-2240  
Fax: +32-3-450-2815  
Pacific: +603-7958-3392  
Fax: +603-7958-5595

<http://www.dowpolyglycols.com>

NOTICE: No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactment. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

