



DURAPLUS™ 3 Floor Finish Polymer

Features & Benefits

- Durability—Formulations based on DURAPLUS™ 3 Floor Finish Polymer have excellent scuff, black heel mark and overall wear resistance.
- Lower costs—Polishes made with DURAPLUS™ 3 Polymer offer decreased labor and equipment costs for end users through a less frequent need to buff, burnish, and recoat, and through a reduction in the number of floor strippings.
- Gloss—DURAPLUS™ 3 Polymer-based formulations have notable lay down gloss and gloss retention.
- Low odor—Polishes made with DURAPLUS™ 3 Polymer have low ammonia odor.
- Detergent resistance and removability—Polishes made with DURAPLUS™ 3 Polymer have an extremely high level of resistance to a variety of harsh detergent solutions. At the same time these polishes maintain the ability to be removed with a mild stripper.

Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

Property	Unit	Result
Appearance		Milky-white liquid
Solids Content	%	38 ± 0.5
Minimum Film-Formation Temperature (MFFT)	°C	~65
pH		8.0–9.0
Viscosity (Brookfield LVT, #1 Spindle, 60 rpm)	cP	< 100
Density @ 25°C	Lb/U.S. gal	~8.8
Specific Gravity		1.07
Ionic Charge		Anionic
Freeze/Thaw Stability	cycles	≥ 3

Description

DURAPLUS™ 3 Polymer is a modified acrylic polymer that offers high gloss and exceptional durability, which are characteristics of DURAPLUS™ polymer technology, and is specially modified to have excellent resistance to harsh detergent solutions. Because it is based on mixed metals crosslinking DURAPLUS™ polymer technology, DURAPLUS™ 3 Polymer offers a level of unsurpassed durability, while also offering very good response to high speed burnishing operations.

Description (Cont.)

Dow offers DURAPLUS™ 3 Polymer-based polishes with a distinct combination of polish hardness, resilience, and an undetectable level of ammonia odor. This helps DURAPLUS™ 3 Polymer-based polishes to dissipate the energy of foot traffic, impacts and abrasion, offering excellent resistance to black marks and scuffing, as well as gloss retention. All of these benefits assure notable labor savings.

Standard Performance Characteristics

As with all Dow floor polish polymers, DURAPLUS™ 3 Polymer shares a number of common performance characteristics.

DURAPLUS™ 3 Polymer facilitates formulating flexibility to offer a range of performance profiles from minimum maintenance to frequent burnishing. The suggested polish formulations made with DURAPLUS™ 3 Polymer meet or exceed an industry slip resistance standard as tested by the Standard Test Method ASTM D-2047. These polishes can be formulated to a range of solids levels from 15 to 25 percent. DURAPLUS™ 3 Polymer offers the manufacture of polishes that can be applied at floor temperatures of 50°F (10°C) and above.

DURAPLUS™ 3 Polymer Formulation DP-3-5 (25%)

Formulation DP-3-5 is a high solids formulation offering high gloss, exceptional durability, and excellent detergent resistance and is an excellent choice for maintenance systems which provide periodic high speed machining. DP-3-5 is formulated with RHOPLEX™ 1531C Emulsion, a high gloss, all-acrylic, alkali-soluble emulsion, which imparts excellent leveling characteristics.

Material in Proper Order of Addition	Percent by Weight	Lb./100 U.S. Gal.	Gal./100 U.S. Gal.
Water	32.42	277.50	33.25
KATHON™ CG/ICP Preservative	0.04	0.34	0.04
Abex 18S (35%) Anionic Surfactant	0.50	4.28	0.50
Capstone FS-65 Fluorosurfactant ¹	0.05	0.42	0.05
CARBITOL™ Solvent, Low Gravity	5.67	48.60	5.88
Eastman TXIB Additive	1.46	12.50	1.59
Tri(butoxyethyl) Phosphate Plasticizer	2.67	22.90	2.70
DURAPLUS™ 3 Polymer	49.56	424.50	48.24
RHOPLEX™ 1531C Emulsion (38%) ²	2.82	24.18	2.75
A-C 540N Ethylene-acrylic Copolymer (30%) ³	3.73	31.99	3.89
A-C 325N Polyethylene Polymer (35%) ⁴	1.06	9.10	1.09
Defoamer ⁵	0.02	0.17	0.02
Totals =>	100.00	856.48	100.00
Formulation Constants	Theoretical Non-volatile Solids		25%
	Theoretical Density, Lb/U.S. Gal		~8.6
	Polymer/Resin/Wax Ratio		88/5/7

1. Recommended Wetting Agent: Capstone FS-65
2. Alternative Alkali Soluble Resins: Michem Dispersion MD-91530
3. Commercial Trade Names: Michem Emulsion 44730 (30%) and BYK wax emulsion, Aquacer 8840 (30%)
4. Commercial Trade Names: Michem Emulsion 93235 (35%) and BYK Wax emulsion Aquacer 8059 (35%)
5. Recommended Defoamer: DEE FO PI-40 Münzing, info@munzing.us

DURAPLUS™ 3 Polymer Formulation DP-3-6 (20%)

Formulation DP-3-6 (20%) is a lower solids version of DP-3-5 offering high gloss, exceptional durability, and excellent detergent resistance and is an excellent choice for maintenance systems which provide periodic high speed machining.

Material in Proper Order of Addition	Percent by Weight	Lb./100 U.S. Gal.	Gal./100 U.S. Gal.
Water	45.91	391.22	46.87
KATHON™ CG/ICP Preservative	0.04	0.34	0.04
Abex 18S (35%) Anionic Surfactant	0.40	3.41	0.40
Capstone FS-65 Fluorosurfactant ¹	0.04	0.34	0.04
CARBITOL™ Solvent, Low Gravity	4.54	38.66	4.68
Eastman TXIB Additive	1.17	9.96	1.27
Tri(butoxyethyl) Phosphate Plasticizer	2.14	18.22	2.15
DURAPLUS™ 3 Polymer	39.64	337.78	38.38
RHOPLEX™ 1531C Emulsion (38%) ²	2.26	19.24	2.19
A-C 540N Ethylene-acrylic Copolymer (30%) ³	2.99	25.46	3.09
A-C 325N Polyethylene Polymer (35%) ⁴	0.85	7.24	0.87
Defoamer ⁵	0.02	0.17	0.02
Totals =>	100.00	852.04	100.00

Formulation Constants		
	Theoretical Non-volatile Solids	20%
	Theoretical Density, Lb/U.S. Gal	~8.5
	Polymer/Resin/Wax Ratio	88/5/7

1. Recommended Wetting Agent: Capstone FS-65
2. Alternative Alkali Soluble Resins: Michem Dispersion MD-91530
3. Commercial Trade Names: Michem Emulsion 44730 (30%) and BYK wax emulsion, Aquacer 8840 (30%)
4. Commercial Trade Names: Michem Emulsion 93235 (35%) and BYK Wax emulsion Aquacer 8059 (35%)
5. Recommended Defoamer: DEE FO PI-40 Münzing, info@munzing.us

DURAPLUS™ 3 Polymer Formulation DP-3-7 (20%)

Formulation DP-3-7 offers high gloss, excellent durability, and detergent resistance. Formulation DP-3-7 has been optimized for maintenance systems requiring frequent high speed machining.

Material in Proper Order of Addition	Percent by Weight	Lb./100 U.S. Gal.	Gal./100 U.S. Gal.
Water	47.05	400.07	47.92
KATHON™ CG/ICP Preservative	0.04	0.34	0.04
Capstone FS-65 Fluorosurfactant ¹	0.04	0.31	0.04
CARBITOL™ Solvent, Low Gravity	4.56	38.75	4.69
Eastman TXIB Additive	1.15	9.77	1.24
Tri(butoxyethyl) Phosphate Plasticizer	2.57	21.84	2.58
DURAPLUS™ 3 Polymer	34.92	296.81	33.73

1. Recommended Wetting Agent: Capstone FS-65

DURAPLUS™ 3 Polymer Formulation DP-3-7 (20%) (Cont.)

Material in Proper Order of Addition	Percent by Weight	Lb./100 U.S. Gal.	Gal./100 U.S. Gal.
RHOPLEX™ 1531C Emulsion (38%) ²	2.26	19.20	2.18
Epolene E43N Polypropylene Polymer (40%) ³	2.53	21.50	2.58
A-C 325N Polyethylene Polymer (35%) ⁴	4.86	41.30	4.98
Defoamer ⁵	0.02	0.17	0.02
Totals =>	100.00	850.06	100.00
Formulation Constants			
	Theoretical Non-volatile Solids		20%
	Theoretical Density, Lb/U.S. Gal		~8.5
	Polymer/Resin/Wax Ratio		79/5/16

2. Alternative Alkali Soluble Resins: Michem Dispersion MD-91530
3. Commercial Trade Names: Michem Emulsion 94340 (40%) and BYK Wax emulsion Aquacer 8940 (40%)
4. Commercial Trade Names: Michem Emulsion 93235 (35%) and BYK Wax emulsion Aquacer 8059 (35%)
5. Recommended Defoamer: DEE FO PI-40 Münzing, info@munzing.us

DURAPLUS™ 3 Polymer Formulation DP-3-8 (20%)

Formulation DP-3-8 offers high gloss, excellent durability, and detergent resistance.

Material in Proper Order of Addition	Percent by Weight	Lb./100 U.S. Gal.	Gal./100 U.S. Gal.
Water	46.56	397.20	47.63
KATHON™ CG/ICP Preservative (1.5%)	0.04	0.34	0.04
Capstone FS-65 Fluorosurfactant ¹	0.04	0.34	0.04
CARBITOL™ Solvent, Low Gravity	4.48	38.22	4.66
Tri(butoxyethyl) Phosphate Plasticizer	2.24	19.11	2.29
DURAPLUS™ 3 Polymer (38%)	40.64	346.74	39.11
Epolene E-43N Polypropylene Emulsion (40%) ²	1.33	11.37	1.42
A-C 325N Polyethylene Polymer (35%) ³	4.65	39.65	4.79
Defoamer ⁴	0.02	0.17	0.02
Totals =>	100.00	853.14	100.00
Formulation Constants			
	Theoretical Non-volatile Solids		20%
	Theoretical Density, Lb/U.S. Gal		~8.5
	Polymer/Resin/Wax Ratio		88/0/12

1. Recommended Wetting Agent: Capstone FS-65
2. Commercial Trade Names: Michem Emulsion 94340 (40%) and BYK Wax emulsion Aquacer 8940 (40%)
3. Commercial Trade Names: Michem Emulsion 93235 (35%) and BYK Wax emulsion Aquacer 8059 (35%)
4. Recommended Defoamer: DEE FO PI-40 Münzing, info@munzing.us

**Handling
Precautions**

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

**Usable Life and
Storage**

Store products in tightly closed original containers at temperatures recommended on the product label.

Limitations

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

**Health and
Environmental
Information**

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, dow.com or consult your local Dow representative.

**Disposal
Considerations**

Dispose in accordance with all local, state (provincial) and federal regulations. Empty containers may contain hazardous residues. This material and its container must be disposed in a safe and legal manner.

It is the user's responsibility to verify that treatment and disposal procedures comply with local, state (provincial) and federal regulations. Contact your Dow Technical Representative for more information.

**Product
Stewardship**

Dow has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Dow products - from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

dow.com

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

