



Technical Data Sheet

SYL-OFF™ SL 560 Coating

Solvent-free silicone release polymer coating

Features & Benefits

- Solvent-free
- Fast curing
- Provides extremely stable release
- Excellent bath stability
- Low release force across a variety of peel speeds
- Requires catalyst addition

Applications

- Release coating for pressure sensitive laminate/labelstock
- Single and double-sided industrial release papers
- Coatings for liners of technical adhesive tapes
- Non-stick foodgrade packaging (see "Food Contact" for specific information)
- Non-stick packaging

Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

Property	Unit	Result
Form		Liquid
Chemical nature		Reactive siloxane polymer
Appearance		Clear liquid
Active ingredients	%	100
Density at 25°C (77°F)	g/cm ³	0.97
Viscosity at 25°C (77°F)	mPa.s	170

Description

Recommendations about how to use and formulate this product with other SYL-OFF™ materials can be obtained from the technical service group.

How To Use

This SYL-OFF™ SL 560 Coating is one component of a multi-component silicone release coating system. In order to use this product effectively, it must be blended with the appropriate SYL-OFF™ release modifiers, catalysts and crosslinkers.

UNRESTRICTED – May be shared with anyone

™ Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow

SYL-OFF™ SL 560 Coating

© 2017 The Dow Chemical Company. All rights reserved.

Handling
Precautions Direct contact with eyes and skin may cause slight irritation which can be relieved by flushing with water for 15 minutes. In the case of eye contact, seek medical attention. Rubber gloves and safety glasses should be worn when handling this product. Do not breathe spray or mist.

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT WWW.CONSUMER.DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

Usable Life And
Storage SYL-OFF SL 560 Coating has a shelf life of 24 months from the date of production.

Packaging
Information Available in a variety of container sizes including bulk totes, drums and sample pails.

Limitations This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

Food Contact
Status This product may comply with certain FDA, BGvV, Kosher or other regulatory agency requirements for food-contact applications.

Health And
Environmental
Information To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, www.consumer.dow.com or consult your local Dow representative.

<http://www.syloff.com>

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DOW SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

DOW DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

