



## Technical Data Sheet

### DOWSIL™ 7695 Adhesive

Pressure sensitive adhesive

#### Features & Benefits

- High peel adhesion on stainless plate
- Very high tack
- High peel adhesion on ultra-low surface tension surface

#### Composition

- Polydimethyl siloxane and resin dispersed in Toluene

#### Applications

- Manufacture of adhesive tapes, labels and transfer/protective films
- PSA for protective film or functional tape on low surface tension substrates like coverglass with anti-fingerprint coating on smartphone, and flexible to mix with other Dow platinum cure PSAs to adjust properties
- Assembly tapes

#### Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

CTM <sup>1</sup>	Property	Unit	Result
0176	Appearance		Clear to slightly hazy, no gels
	Physical form		Liquid
	Diluent		Toluene
0208	Non-volatile content	%	63
0050	Viscosity at 25°C (77°F)	cP	14600
	Specific gravity at 25°C (77°F)		0.98
	Adhesion <sup>2</sup>	oz/in	50

1. CTM: Corporate Test Method, copies of CTM's are available on request.
2. 30 um dry thickness adhesive on 50 um thickness PET film; 0.1% SYL-OFF™ SL 7028 Crosslinker, 0.6% SYL-OFF™ 397 Anchorage Additive, 1.4% SYL-OFF™ 4000 Catalyst; curing cycle 1 minute at 150°C; tape laminated on SUS, 0.3 m/m, 180-degree angle.

#### Description

DOWSIL™ 7695 Adhesive is a silicone pressure sensitive adhesive that, when used with SYL-OFF™ 4000 Catalyst, offers the ability to make silicone pressure sensitive tapes or protective films. When cured on substrates, DOWSIL™ 7695 Adhesive could give high tack and high peel adhesion. The product also has high peel adhesion on low surface tension surfaces like coverglass with anti-fingerprint coating on smartphone.

## How to Use

DOWSIL™ 7695 Adhesive normally uses 0~0.5% SYL-OFF™ SL 7028 Crosslinker and 1.0~1.4% SYL-OFF™ 4000 Catalyst for catalyzing. This adhesive is dispersed in toluene with 63% non-volatile content (the range is 61–65%). It can be further diluted in compatible solvent like toluene, heptane, ethyl acetate, MEK, mixture solvent with aliphatic solvent etc.

The following procedure is recommended for the preparation of coating bath. Equipment should be clean and dry, preferably constructed from stainless steel or glass. Disperse DOWSIL™ 7695 Adhesive in the process solvent. The suggested bath solids are 35 to 55% silicone on a weight basis.

This adhesive can be coated onto backing with traditional coating equipment.

When diluting with any solvent, refer to the solvent vendor's safety data sheet for information on physical and health hazards associated with the solvent and use of ventilation, PPE, bonding and grounding or other measures that can minimize or eliminate these risks.

### Anchorage to Backing

SYL-OFF™ anchorage additives like SYL-OFF™ 397 Anchorage Additive, SYL-OFF™ 297 Anchorage Additive and SYL-OFF™ 9250 Anchorage Additive can be used to improve the anchorage with backings. And if necessary, a primer may be used to get optimum anchorage.

## Bath Life

The life of the formulated bath varies considerably with bath concentration, the solvent, the specific formulation, and the temperature of the surroundings. Under normal bath condition at room temperature the bath should be used up within 6 hours.

## Cure

When used in the manufacture of pressure sensitive constructions, catalyzed DOWSIL™ 7695 Adhesive is normally coated onto flexible substrates such as polyester and be cured at over 120°C in a vented, continuous coating oven. Air flow patterns, air volume and velocity will have an impact on adhesive curing speed. The insufficient temperature can cause poor cohesion and not good stability by uncured adhesive. The excess amount of catalyst causes a short bath life.

Note: The catalyst in this adhesive system is required to obtain pressure sensitive properties. It is also subject to contamination by peroxides and other chemical residues. Clean all mixing and coating equipment and use dedicated new containers for mixing when possible.

## Handling Precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

## Usable Life and Storage

When stored at ambient temperature in the original unopened containers, this product has a usable life of 12 months from the date of production.

**Packaging Information**

This product is available in a variety of container sizes. Contact the local Dow customer service about the container size information.

**Limitations**

Shipping: DOT Classification: flammable.

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

**Health and Environmental Information**

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, [dow.com](http://dow.com) or consult your local Dow representative.

**Disposal Considerations**

Dispose in accordance with all local, state (provincial) and federal regulations. Empty containers may contain hazardous residues. This material and its container must be disposed in a safe and legal manner.

It is the user's responsibility to verify that treatment and disposal procedures comply with local, state (provincial) and federal regulations. Contact your Dow Technical Representative for more information.

**Product Stewardship**

Dow has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Dow products - from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

**Customer Notice**

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

[dow.com](http://dow.com)

**NOTICE:** No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

