



REDI-LINK™ DFDA-5430 NT

Catalyst Masterbatch for Moisture Curable Power Cable Insulation

Overview

REDI-LINK™ PE is a two component moisture curable crosslinkable system for use in low voltage power cable applications. DFDA-5440 Natural, with a density of 0.922, may be crosslinked after extruding with the DFDA-5430 Natural catalyst masterbatch, with a density of 0.921, in a 50:50 ratio and then allowing moisture to diffuse into the insulation. If a black product is required, the addition of DFDB-5410 Black 55 carbon black masterbatch to DFDA-5430 Natural and DFDA-5440 Natural is recommended.

Specifications

When DFDA-5440 Natural is crosslinked with DFDA-5430 Natural and optionally, DFDB-5410 Black 55, it meets typical low voltage specifications such as those found in:

- IEC-60502
- GB 12706-91
- IS 7098 - 1988

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength	2390 psi	16.5 MPa	IEC 60811-1-2
Tensile Elongation (Break)	350 %	350 %	IEC 60811-1-2
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Hot Set ¹	< 100 %	< 100 %	IEC 60811-2-1
Aging	Nominal Value (English)	Nominal Value (SI)	Test Method
Retention of Tensile Elongation - 7 days 275°F (135°C)	> 85 %	> 85 %	IEC 60811-1-2
Retention of Tensile Strength - 7 days 275°F (135°C)	> 85 %	> 85 %	IEC 60811-1-2
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Volume Resistivity	2.0E+16 ohms·cm	2.0E+16 ohms·cm	IEC 60502
Insulation Resistance	71400 Mohms·km	71400 Mohms·km	IEC 60502

Additional Information

Storage:

- The environment or conditions of storage greatly influences the recommended storage time. Storage under extreme conditions may affect the quality, processing, or performance of the product. Storage should be in accordance with good manufacturing practices. The recommended storage conditions are dry conditions with temperatures between 50°F and 86°F (10°C and 30°C). When stored under these conditions, the product may be used by the customer for up to one year from the date of sale or two years from the date of manufacture, whichever comes first. It is recommended that the practice of using the product on a first-in / first-out basis be established.

Extrusion	Nominal Value (English)	Nominal Value (SI)
Melt Temperature	356 to 392 °F	180 to 200 °C

Extrusion Notes

REDI-LINK PE is designed primarily for colourable applications and can be processed on any modern thermoplastic extruder. Prior to extrusion, DFDA-5430 Natural and DFDA-5440 Natural are blended together in a 50:50 ratio. Melt temperatures between 180°C and 200°C have been used successfully. For applications requiring weather resistance, the addition of 6.3% DFDB-5410 Black 55, the carbon black masterbatch, to the natural REDI-LINK PE system is recommended. It is especially recommended that the carbon black masterbatch be dried at 60-70°C for four to six hours using dehumidified air prior to mixing and extrusion. This will ensure that REDI-LINK PE will extrude with excellent surface quality and without extrusion scorch.

After extrusion of the appropriate mixture of this product, crosslinking can be achieved by allowing moisture to diffuse into the product. Most fabricators find that a hot water bath or sauna works best.

Notes

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

¹ Cured in 90°C water, 0.8 mm wall, 8 hr

Product Stewardship

The Dow Chemical Company and its subsidiaries ("Dow") has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our Product Stewardship program rests with each and every individual involved with Dow products — from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

Medical Applications Policy

NOTICE REGARDING MEDICAL APPLICATION RESTRICTIONS: Dow will not knowingly sell or sample any product or service ("Product") into any commercial or developmental application that is intended for:

- long-term or permanent contact with internal bodily fluids or tissues. "Long-term" is contact which exceeds 72 continuous hours;
- use in cardiac prosthetic devices regardless of the length of time involved ("cardiac prosthetic devices" include, but are not limited to, pacemaker leads and devices, artificial hearts, heart valves, intra-aortic balloons and control systems, and ventricular bypass-assisted devices);
- use as a critical component in medical devices that support or sustain human life; or
- use specifically by pregnant women or in applications designed specifically to promote or interfere with human reproduction.

Dow requests that customers considering use of Dow products in medical applications notify Dow so that appropriate assessments may be conducted. Dow does not endorse or claim suitability of its products for specific medical applications. It is the responsibility of the medical device or pharmaceutical manufacturer to determine that the Dow product is safe, lawful, and technically suitable for the intended use. **DOW MAKES NO WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF ANY DOW PRODUCT FOR USE IN MEDICAL APPLICATIONS.**

Disclaimer

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the Customer is responsible for determining whether products and the information in this document are appropriate for the Customer's use and for ensuring that the Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Dow assumes no obligation or liability for the information in this document. **NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**

NOTICE: If products are described as "experimental" or "developmental": (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; (3) there is greater potential for Dow to change specifications and/or discontinue production; and (4) although Dow may from time to time provide samples of such products, Dow is not obligated to supply or otherwise commercialize such products for any use or application whatsoever.

NOTICE: This data is based on information Dow believes to be reliable, as demonstrated in controlled laboratory testing. They are offered in good faith, but without guarantee, as conditions and method of use of Dow products are beyond Dow's control. Dow recommends that the prospective user determine the suitability of these materials and suggestions before adopting them on a commercial scale.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability for the accuracy and completeness of such information.

Additional Information

North America		Europe/Middle East	+800-3694-6367
U.S. & Canada:	1-800-441-4369		+31-11567-2626
	1-989-832-1426	Italy:	+800-783-825
Mexico:	+1-800-441-4369		
Latin America		South Africa	+800-99-5078
Argentina:	+54-11-4319-0100		
Brazil:	+55-11-5188-9000		
Colombia:	+57-1-219-6000	Asia Pacific	+800-7776-7776
Mexico:	+52-55-5201-4700		+603-7965-5392

www.dowplastics.com

This document is intended for use within Africa & Middle East, Asia Pacific

Published: 2005-11-17

© 2019 The Dow Chemical Company

