



INTREPID™ 2499 NT

Bimodal Polyethylene Resin

Overview

INTREPID™ 2499 NT Bimodal Polyethylene Resin is a Polyethylene resin produced with raised temperature capability (PE-RT) using UNIPOL™ II process technology. This product is intended for use in municipal and industrial piping systems where extreme conditions such as high temperatures, aggressive chemicals, hydrocarbons, or highly oxidative conditions exist. Suitable uses include oil and gas field pipelines, gas distribution pipelines, mining pipelines, district heating systems, municipal water distribution and other industrial applications.

Industrial Standards Compliance:

ASTM D3350: cell classification:

- Natural - PE445574A CCO
- Black - PE445574C CC3 (See Notes A and B)

Plastics Pipe Institute (PPI): TR-4

- Natural Pipe INTREPID 2499 NT Bimodal Polyethylene Resin
- ASTM PE4710 pipe grade - 1600psi HDB @ 73 °F (23°C)
- ASTM PE4710 pipe grade - 800psi HDB @ 180 °F (82.2°C)
- Black Pipe INTREPID 2499 BK Bimodal Polyethylene Resin (See Note B)
- ASTM PE4710 pipe grade - 1600psi HDB @ 73 °F (23°C)
- ASTM PE4710 pipe grade - 800psi HDB @ 180 °F (82.2°C)

NSF International: Standard 14 and 61

- Natural Pipe INTREPID 2499 NT
- Black Pipe INTREPID 2499 BK (See Note B)

NOTES:

(A) The first 5 numbers of the cell classification are based on natural resin. The last number and letter are based on black resin. (natural resin plus 6.5% DFNF-0092).

(B) Natural resin extruded under proper conditions with carbon black masterbatch DFNF-0092 BK (6.5%)

Additive

- Antiblock: No
- Slip: No
- Processing Aid: Yes

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density			ASTM D792
Natural	0.950 g/cm ³	0.950 g/cm ³	
Black ¹	0.960 g/cm ³	0.960 g/cm ³	
Melt Index			ASTM D1238
190°C/2.16 kg	0.10 g/10 min	0.10 g/10 min	
190°C/21.6 kg	7.0 g/10 min	7.0 g/10 min	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength ² (Yield)	> 3500 psi	> 24.1 MPa	ASTM D638
Tensile Elongation ² (Break)	> 500 %	> 500 %	ASTM D638
Flexural Modulus ^{3,2}	152000 psi	1050 MPa	ASTM D790B
Resistance to Rapid Crack Propagation, P _c			
Full Scale : 32°F (0°C) ⁴	> 663 psi	> 45.7 bar	ISO 13478
S-4 : 32°F (0°C) ⁵	> 174 psi	> 12.0 bar	
Resistance to Rapid Crack Propagation, T _c - S-4 ⁴			ISO 13478
32°F (0°C)	< 1 °F	< -17 °C	
Slow Crack Growth PENT - @ 2.4 MPa ²			ASTM F1473
176°F (80°C)	10000 hr	10000 hr	
194°F (90°C)	6000 hr	6000 hr	
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact ² (73°F (23°C))	9.1 ft-lb/in	490 J/m	ASTM D256A

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Brittleness Temperature ²	< -103 °F	< -75.0 °C	ASTM D746A
Melting Temperature (DSC)	269 °F	132 °C	Dow Method
Thermal Stability	> 428 °F	> 220 °C	ASTM D3350

Extrusion Notes

Fabrication Conditions:

- Screw Type: High quality HDPE barrier with mixing
- Melt Temperature Range: 380-450°F (193-232°C)

Notes

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

¹ Natural resin extruded under normal conditions with carbon black masterbatch DFNF-0092 (6.5%)

² Compression molded parts prepared according to ASTM D 1928 Procedure C. Properties will vary with changes in molding conditions and aging time.

³ Method I (3 point load)

⁴ Calculated value, determined by the equation in ISO 4437 based on S-4 test data. Pipe diameter of 10 inch IPS (25.4 cm) and Standard Diameter Ratio (SDR) 11

⁵ Pipe diameter of 10 inch IPS (25.4 cm) and Standard Diameter Ratio (SDR) 11.

Product Stewardship

The Dow Chemical Company and its subsidiaries ("Dow") has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our Product Stewardship program rests with each and every individual involved with Dow products — from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

Medical Applications Policy

NOTICE REGARDING MEDICAL APPLICATION RESTRICTIONS: Dow will not knowingly sell or sample any product or service ("Product") into any commercial or developmental application that is intended for:

- long-term or permanent contact with internal bodily fluids or tissues. "Long-term" is contact which exceeds 72 continuous hours;
- use in cardiac prosthetic devices regardless of the length of time involved ("cardiac prosthetic devices" include, but are not limited to, pacemaker leads and devices, artificial hearts, heart valves, intra-aortic balloons and control systems, and ventricular bypass-assisted devices);
- use as a critical component in medical devices that support or sustain human life; or
- use specifically by pregnant women or in applications designed specifically to promote or interfere with human reproduction.

Dow requests that customers considering use of Dow products in medical applications notify Dow so that appropriate assessments may be conducted. Dow does not endorse or claim suitability of its products for specific medical applications. It is the responsibility of the medical device or pharmaceutical manufacturer to determine that the Dow product is safe, lawful, and technically suitable for the intended use. **DOW MAKES NO WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF ANY DOW PRODUCT FOR USE IN MEDICAL APPLICATIONS.**

Disclaimer

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the Customer is responsible for determining whether products and the information in this document are appropriate for the Customer's use and for ensuring that the Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Dow assumes no obligation or liability for the information in this document. **NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**

NOTICE: If products are described as "experimental" or "developmental": (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; (3) there is greater potential for Dow to change specifications and/or discontinue production; and (4) although Dow may from time to time provide samples of such products, Dow is not obligated to supply or otherwise commercialize such products for any use or application whatsoever.

NOTICE: This data is based on information Dow believes to be reliable, as demonstrated in controlled laboratory testing. They are offered in good faith, but without guarantee, as conditions and method of use of Dow products are beyond Dow's control. Dow recommends that the prospective user determine the suitability of these materials and suggestions before adopting them on a commercial scale.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability for the accuracy and completeness of such information.

Additional Information

North America		Europe/Middle East	+800-3694-6367
U.S. & Canada:	1-800-441-4369		+31-11567-2626
	1-989-832-1426	Italy:	+800-783-825
Mexico:	+1-800-441-4369		
Latin America		South Africa	+800-99-5078
Argentina:	+54-11-4319-0100		
Brazil:	+55-11-5188-9000		
Colombia:	+57-1-219-6000	Asia Pacific	+800-7776-7776
Mexico:	+52-55-5201-4700		+603-7965-5392

www.dowplastics.com

This document is intended for use within Europe, Latin America, North America

Published: 2012-07-11

© 2019 The Dow Chemical Company

