



Technical Data Sheet

**SILASTIC™ 9252/900P**

38 Durometer, two-part, 1 to 1 mix, translucent, fabric coating grade liquid silicone rubber

**Features & Benefits**

- Good clarity
- Easily pigmentable
- Formulated to meet BgVV, XV and FDA 21 CFR 177.2600
- Unprimed adhesion to glass fabric

**Applications**

- Fabric coating
- Electrical-wire sleeving
- Suitable for food contact

**Typical Properties**

Specification Writers: These values are not intended for use in preparing specifications.

Test <sup>1</sup>	Property	Unit	Result	
<b>As supplied</b>				
	Solids content	%	100	
	Mixed viscosity	mPa.s	90,000	
			<b>As molded</b>	<b>Post-cured</b>
D792	Specific gravity		1.13	1.13
D2240	Hardness	Shore A	37	41
D412 DIE C	Tensile strength	Mpa	6.0	7.4
D412 DIE C	Elongation at break	%	450	380
D624 DIE B	Tear strength	kN/m	14	15
D257	Volume resistivity	Ohm.cm	3.4x10 <sup>15</sup>	

Properties obtained on 2 mm thick slabs: Press cured 10 minutes at 120°C (248°F).  
 Post-cured 4 hours at 200°C (392°F).  
 Viscosity measured on the Brookfield HAF Viscometer, spindle 7, 10 r.p.m.

1. ASTM: American Society for Testing and Materials. Materials were tested according to Dow Corporate Test Methods (CTM), which in most cases are similar to the ASTM standard listed above.

## How To Use

### Mixing and De-Airing

The A and B components are supplied strained and de-aired to be used as lot matched kits.

Mix parts A and B in a 1:1 ratio. Meter mix equipment which pumps, meters and mixes the two components without the incorporation of air is strongly recommended for production. If air bubbles are entrapped during mixing the mixture must be thoroughly de-gassed under vacuum.

### Pot Life

When parts A and B are mixed the mixture will remain usable for 72 hours at 25°C (77°F).

### Cleaning

The uncured silicone can readily be removed by most hydrocarbon solvents. Polar solvents, such as ketones and alcohols, are not suitable.

### Curing

SILASTIC™ 9252/900P cures rapidly at elevated temperatures. A 2 mm cross-section requires 8–14 seconds at 200°C (392°F). The cure time depends on the thickness and the cure temperature used. Cure can be inhibited by contact with certain materials such as amines, sulphur and tin complexes.

### Pigmentation

This is normally carried out during mixing and dispensing of the two components. SILASTIC™ LPX Liquid Color Masterbatches are recommended with normal addition levels of 2 to 4% based on total volume.

## Handling Precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT WWW.DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

## Usable Life And Storage

When stored at or below 32°C (90°F) in the original unopened containers, this product has a usable life of 15 months from the date of production.

## Packaging Information

This product is supplied in lot matched kits: in pails (20 kg) and in drums (205 kg).

## Food Contact

This product has been formulated to meet applicable food contact regulations and recommendations (for example: FDA 21.CFR 177.2600 and BgVV, XV). For further details on the suitability of this product for food contact applications, please refer to the Food Regulatory Profile.

Post cure is recommended to ensure that food contact requirements are met.

Note: It remains the manufacturers' responsibility to test the final product.

## Limitations

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

## **Health And Environmental Information**

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, [www.dow.com](http://www.dow.com) or consult your local Dow representative.

## **Disposal Considerations**

Dispose in accordance with all local, state (provincial) and federal regulations. Empty containers may contain hazardous residues. This material and its container must be disposed in a safe and legal manner.

It is the user's responsibility to verify that treatment and disposal procedures comply with local, state (provincial) and federal regulations. Contact your Dow Technical Representative for more information.

## **Product Stewardship**

Dow has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Dow products - from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

## **Customer Notice**

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

[dow.com](http://dow.com)

**NOTICE:** No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

