



Technical Data Sheet

DOWSIL™ 3441 Two-Part Fast Cure Workshop Silicone Sealant

Features & Benefits

- When used correctly, fast gluing and short storage times will be achieved due to the fast development of high strength
- Outstanding adhesion to a wide range of substrates including PVC-U, aluminum and glass
- Excellent resistance to UV radiation
- Excellent temperature stability: -30°C (-22°F) to +90°F
- High levels of mechanical properties
- Low water absorption
- Odorless and non-corrosive cure system
- Resistant to ozone

Applications

- This product is suitable for framing and glazing applications to ensure a good seal between glass and frame. It is formulated to develop an excellent primerless adhesion and fast gluing properties to various substrates like aluminum, wood and especially PVC-U. The high performance features incorporated into this product make it especially suitable for the following applications:
 - Glass-sash backbedding application
 - Gluing to increase rigidity of construction parts
 - Fast curing deep sealant joints.

Not suitable for "Structural Glazing" applications. For "Structural Glazing" applications, DOWSIL™ 993 should be used.

Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

Property	Unit	Result
Base: as supplied		
Color and consistency		Viscous white paste
Specific gravity	g/ml	1.36
Viscosity (100s ⁻¹)	mPa.s	160,000

UNRESTRICTED – May be shared with anyone

®™ Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow

DOWSIL™ 3441 Two-Part Fast Cure Workshop Silicone Sealant

© 2017 The Dow Chemical Company. All rights reserved.

Typical Properties (Cont.)

Property	Unit	Result
Curing agent: as supplied		
Color and consistency		Clear yellow paste
Specific gravity	g/ml	0.98
Viscosity (100s ⁻¹)	mPa.s	15,000
Flammability -flash point	°C	13
	°F	55
As catalized		
Mixing ratio by weight (base/curing agent)		9:1 and 11:1 w/w (depending on the cure speed needed)
Color and consistency		Beige non-slumping paste
Working time (25°C/77°F, 50% R.H.)	minutes	20 to 40
Tack-free time (25°C/77°F, 50% R.H.)	minutes	90 to 240
Specific gravity	g/ml	1.35
After 3 days cure		
Hardness	Shore A	35
12 x 12 x 50 mm³ size T.A. joint (ISO 8339)¹		
Young modulus	MPa	1.8
100% modulus	MPa	1
Tensile strength	MPa	1.1
¹ Lot matching of base and curing agent not necessary Manufactured under ISO 9000 series		

1. ISO: International Standardisation Organisation.

Description

DOWSIL™ 3441 Two-Part Fast Cure Workshop Silicone Sealant is a two-component neutral curing silicone sealant specifically developed for the bonding of insulated glass units into pvc-u profiles to increase the frame rigidity.

The improved stability of DOWSIL 3441 Two-Part Fast Cure Workshop Silicone Sealant at elevated temperatures, UV and humidity as well as its higher young modulus will ensure long lasting performance. Neutral alkoxy; cures at room temperature giving off a small amount of alcohol.

Water pick-up (%): 0.5 after 60 days water immersion at 60°C (140°F).

How To Use

Mixing and dispensing instructions

DOWSIL 3441 Two-Part Fast Cure Workshop Silicone Sealant should be mixed in a ratio of 10:1 base to curing agent by weight, or equivalent 7.9:1 by volume for optimal properties. At this mix ratio, the sealant typically exhibits a working time of 20 minutes and allows the assembly to be handled within four hours. Slight variations in mixing ratio can be tolerated, but these should not exceed 11:1 to 9:1 by weight to ensure minimum properties are obtained. The sealant is compatible with most of DOWSIL neutral curing construction sealants. Please contact our technical services department for more information.

UNRESTRICTED – May be shared with anyone

®™ Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow

DOWSIL™ 3441 Two-Part Fast Cure Workshop Silicone Sealant

© 2017 The Dow Chemical Company. All rights reserved.

How To Use (Cont.)

To obtain the ultimate physical properties from DOWSIL 3441 Two-Part Fast Cure Workshop Silicone Sealant it is recommended that the base and curing agent are thoroughly mixed using an airless mixing system found on most existing commercially available two-part silicone dispensing machines. In case of smaller applications only special two-part hand-mixing cartridge systems (Semco/CAS) should be used to avoid incorporation of air into the material.

DOWSIL 3441 Curing Agent will react with atmospheric moisture and therefore should not be exposed to air for prolonged periods of time.

Curing agent

The curing agent is a semi-viscous paste and is suitable for meter mix equipment that uses a follower plate transfer pump system for the catalyst.

Curing agent will react with atmospheric moisture and therefore should not be exposed to air for prolonged periods of time. It is strongly recommended that the curing agent be agitated before use to ensure homogeneity of all components.

Equipment cleaning when not being used it is recommended that the dispensing equipment be purged either with the uncatalyzed base, or flushed with a suitable solvent such as DOWSIL™ 3522 Concentrated Cleaning Solvent. If cured sealant has built up inside the equipment, it is recommended to flush the equipment for the appropriate time with DOWSIL 3522 Concentrated Cleaning Solvent using a solvent recirculation system. This solvent dissolves cured silicone sealant and provides optimum cleaning performance.

Handling Precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT WWW.CONSUMER.DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

Usable Life And Storage

When stored between 5°C (41°F) and 25°C (77°F) in the original unopened containers, DOWSIL 3441 Curing Agent has a usable life of 12 months from the date of production.

When stored at or below 25°C (77°F) in the original unopened containers, DOWSIL 3441 Base has a usable life of 12 months from the date of production.

Packaging Information

DOWSIL 3441 Base is available in 250 kg drums. DOWSIL 3441 Catalyst is available in 25 kg pails.

Limitations

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

The sealant cannot be used for structural glazing of glass units to a metal frame, or as a sealant for insulating glass units.

UNRESTRICTED – May be shared with anyone

®™ Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow

DOWSIL™ 3441 Two-Part Fast Cure Workshop Silicone Sealant

© 2017 The Dow Chemical Company. All rights reserved.

Health And Environmental Information

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, www.consumer.dow.com or consult your local Dow representative.

<http://www.consumer.dow.com>

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DOW SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

DOW DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

