



SILASTIC™ RBL-9694-30P Liquid Silicone Rubber

Two-part silicone elastomer for integrated compression seals

Features & Benefits

- Two-part addition cure silicone elastomer
- Hardness suitable for sealing applications under medium clamping loads
- Non-sag nature yields accurate, uniform gasket beads of precise dimensions as defined by robot application parameters
- User-friendly, easy to handle 1:1 mix ratio
- Fast cure at elevated temperatures, no post-curing
- Low compression set
- Good adhesion to many substrates
- Long term stability over a wide temperature range (-50°C to 200°C)
- Does not require solvents, CFCs or other environmentally harmful materials for processing

Applications

- SILASTIC™ RBL-9694-30P Liquid Silicone Rubber is designed to be dispensed and cured directly on automotive and other industrial components to form integrated gaskets.
- Typical applications include gaskets for components which require medium clamping forces, e.g. intake systems, front covers and throttle valves.

Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

CTM ¹	ASTM ²	Property	Unit	Result	
				Part A	Part B
		As supplied			
0176		Consistency		Pumpable paste	Pumpable paste
0063		Color		Black	White
0364	MIL-S 8802D	Extrusion rate ³	g/minute	75	178
0090A	D56	Flash point - closed cup	°C	> 100	> 100

1. CTM: Corporate Test Method, copies of CTMs are available on request
2. ASTM: American Society for Testing and Materials
3. Extrusion rate: 3.2 mm nozzle at 0.63MPa

Typical Properties (Cont.)

CTM	ASTM	Property	Unit	Result	
As mixed 1:1 ratio				Part A	Part B
0063		Color		Grey	
0097	D1298	Specific gravity		1.20	
1059	D5289	Cure time T90% (115°C)	s	46	92
As cured (5 minutes 150°C) - physical properties					
0099	D2240	Durometer hardness, Shore A		32	
0137	D412C	Tensile strength, Die C	MPa	7.2	
0137	D412C	Elongation at break	%	820	
0137	D412C	Modulus 100%	MPa	0.80	
0159	D624B	Tear strength, Die B	kN/m	14	
0085	D395B	Compression set, -25% compression for 22 hours at 177°C	%	31	
0243	D816	Lap shear adhesion (10 minutes 150°C) on aluminum	MPa	1.0	
As supplied					
		On PA 66 GF 30	MPa	1.6	
		On vinyl ester	MPa	1.2	

Description

SILASTIC™ RBL-9694-30P Liquid Silicone Rubber is a two-part heat-cure silicone elastomer, designed to be easily mixed and dispensed via meter-mix equipment. It is cured directly on automotive and other industrial components to form an integrated, high strength compression seal. It is resistant to many industrial fluids (e.g. engine oils, water/glycol mixtures) over a broad temperature range with the exception of fuels and non-polar solvents.

The Cured-in-Place-Gasket Concept (CIPG)

The 'Cured-in-Place-Gasket' concept made possible with SILASTIC™ RBL-9694-30P Liquid Silicone Rubber provides a successful alternative to traditional gasketing methods using manually installed preformed rubber gaskets. This approach provides greater design flexibility as the robotically applied liquid silicone beads can easily follow complex surface geometries.

Additionally, changes in part design can be rapidly accommodated by reprogramming the dispensing system. The extruding seals are applied and positioned with excellent reproducibility time after time, ensuring good sealing performance. Equally important, the sealing/curing process lends itself ideally to a continuous, fully automated operation thus providing meaningful savings on the costs associated with manual gasket installation.

How to Use

Substrate Preparation

SILASTIC™ RBL-9694-30P Liquid Silicone Rubber adheres to many metallic and plastic substrates (normally without using primer). This feature ensures the cured gaskets will not be displaced during packaging or handling of the sealed component. Regardless of the substrate, the sealing surfaces should be clean and free of dirt, oils, and release agents to ensure good adhesion. In most instances washing with water based industrial detergents will remove these contaminants. Some substrates however will require additional treatment to achieve good adhesion. This could mean plasma, corona, flame treatment or chemical priming.

How to Use (Cont.)

Processing

SILASTIC™ RBL-9694-30P Liquid Silicone Rubber is optimally mixed, dispensed and applied to the components to be sealed using a fully automated and integrated process.

Metering/Mixing

The mixing step is successfully carried out with commercially available two component meter-mix pumps designed to work on a 1:1 weight ratio. The A and B components are pumped from pails or drums using follower-plate mounted piston pumps, then fed into smaller, precise gear or piston pumps where the actual metering takes place. The precisely metered A and B components are then mixed by means of standard multi-element static mixers. The working time of the A/B mixture at room temperature is about 4–6 hours and this eliminates the danger of blocking the mixer with cured product during normal production stops.

Application

For automated bead application the mixing head is attached to a robotic arm or alternatively the wrist applicator of an XYZ table gantry. Typically the meter-mix equipment and the robot or XYZ table are fully integrated in a system which dispenses precisely metered volumes of uncured elastomer in a preprogrammed path onto the component to be sealed. The desired bead dimensions are achieved by a combination of parameters involving the pump throughput rate, the dispensing head diameter and tip speed, and the distance from tip to component surface.

The non-sag nature of SILASTIC™ RBL-9694-30P Liquid Silicone Rubber ensures that the dispensed bead dimensions remain unchanged after the bead is cured. The gasket bead size is a function of the sealing gap and the flange width.

Curing

Curing and adhesion of SILASTIC™ RBL-9694-30P Liquid Silicone Rubber gasket beads are achieved by submitting the uncured elastomer to a temperature of 150°C for 6–8 minutes. In an automated process the components to be sealed will typically be mounted on a conveyor system and the bead applied by robot with a typical cycle time of 10 to 45 seconds per component (depending on size). The gasket beads are then cured by passing the sealed components through a heating tunnel.

The required cure time of 6–8 minutes is obtained by appropriate dimensioning of the tunnel length for a given conveyor speed. A particularly efficient way to transfer heat to the elastomer for effective curing, and to minimize heat dissipation in the mass of the component, is the use of focused infrared heating elements.

Handling Precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

Usable Life and Storage

Product should be stored at or below 35°C (95°F) in original, unopened containers.

Limitations

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

Health and Environmental Information

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, dow.com or consult your local Dow representative.

Disposal Considerations

Dispose in accordance with all local, state (provincial) and federal regulations. Empty containers may contain hazardous residues. This material and its container must be disposed in a safe and legal manner.

It is the user's responsibility to verify that treatment and disposal procedures comply with local, state (provincial) and federal regulations. Contact your Dow Technical Representative for more information.

Product Stewardship

Dow has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Dow products - from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

Heat Ageing and Fluid Immersion Resistance

As cured - heat aged		
Hot air, 2016 hours at 150°C		
Change in hardness	points	+5
Change in tensile strength	%	-8
Change in elongation	%	-28
Change in modulus at 100%	%	+15
Hot air, 1008 hours at 200°C		
Change in hardness	points	+4
Change in tensile strength	%	-19
Change in elongation	%	-38
Change in modulus at 100%	%	+46

Heat Ageing and Fluid Immersion Resistance (Cont.)

As cured - fluid immersion resistance

BASF Glysantin/Water 1:1, 1008 hours at 108°C

Change in hardness	points	0
Change in tensile strength	%	-14
Change in elongation	%	-15
Change in modulus at 100%	%	+12
Volume swell	%	+1.6

ASTM #1 Oil, 1008 hours at 150°C

Change in hardness	points	-7
Change in tensile strength	%	-28
Change in elongation	%	-32
Change in modulus at 100%	%	+11
Volume swell	%	+6

Shell TMO 10W-40, 1008 hours at 150°C

Change in hardness	points	-16
Change in tensile strength	%	-63
Change in elongation	%	-47
Change in modulus at 100%	%	-27
Volume swell	%	+25

As cured - compression stress relaxation¹

Retention of the initial sealing force (initial value = 100%)

Hot air, 1008 hours at 150°C	37
BASF Glysantin/Water 1:1, 1008 hours at 105°C	58
ASTM #1 oil, 1008 hours at 150°C	22
ASTM #3 oil, 1008 hours at 150°C	8
Wintershall Referenz 15W-40, 1008 hours at 150°C	11
BP Strato 10W-40, 1008 hours at 150°C	6

¹According to DIN 53 537, punched rings with rectangular cross-section, test medium only inside

dow.com

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

