

# THE DOW CHEMICAL COMPANY SALES SPECIFICATION

**Date Printed:** 2024-05-18

Effective Date: 2018-10-31 Supersedes Date: 2018-10-31

Name: DOWSIL™ Contractors Weatherproofing Sealant, Bronze

**Specification Number:** 000000841813

#### Shelf Life

Container Type	Conditions of	Conditions of	Shelf	Deterioration
	Handling	Storage	Life	Characteristics
All Approved Packaging	Refrigerate > 7 days	Store BELOW 27C/81F	540 Days	

### **Final Testing Requirements**

Test and Test Condition	Limit	Unit	Method	Note
Appearance, uniform viscous paste	Pass		CTM0176	
Tack free time	360 Max	min	CTM0095	
Extrusion rate	75 Min	g/min	CTM0364	
Flow Test Frequency:	0.2 Max audit once per year	inch	CTM0062	
Durometer, 7d/RT	25 Min	ShoreA	CTM0099	
Tensile, 7d/RT	125 Min	psi	CTM0137A	
Elongation, 7d/RT	450 Min	%	CTM0137A	
Tear Die B, 7d/RT	20 Min	lb/in	CTM0159A	

<sup>&</sup>lt;sup>®</sup> ™ Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow

## THE DOW CHEMICAL COMPANY SALES SPECIFICATION

Name: DOWSIL™ Contractors Weatherproofing Sealant, Bronze

**Specification Number:** 000000841813 **Effective Date:** 2018-10-31

#### **External Notes**

1 Dow Chemical warrants that the above designated material conforms to the listed sales specifications even though there may be no value reported.

Test Item Limits Flow <=0.2 inches Durometer (7d/RT) >=25 Shore A Tensile (7d/RT) >=125 psi Elongation (7d/RT) >=450 % Tear (7d/RT) >=20 lb/inch

READ PRECAUTIONARY INFORMATION AND MATERIAL SAFETY SHEETS. THIS PRODUCT IS SHIPPED IN COMPLIANCE WITH APPLICABLE LAWS AND REGULATIONS REGARDING CLASSIFICATION, PACKAGING, SHIPPING AND LABELING.