

#### **Technical Data Sheet**

## **DOWSIL™ 732 RTV Adhesive Sealant**

General purpose silicone adhesive/sealant (specified)

# Features & **Benefits**

- One-component adhesive/sealant
- Cures at room temperature when exposed to moisture in the air
- Acetoxy cure system
- Non-sag, paste consistency
- Easy to apply
- Cures to a tough, flexible rubber
- Good adhesion to many substrates
- Stable and flexible from -60°C to +180°C (-76°F to +356°F), with short peaks up to +205°C (401°F)
- Black version: stable and flexible from -60°C to +205°C (-76°F to +401°F), with short peaks up to +230°C (446°F)
- Excellent dielectric properties
- Complies with MIL-A-46106
- Complies with FDA 177.2600
- Available in white, black, clear and aluminum

#### **Applications**

General industrial sealing and bonding applications

## **Typical Properties**

Specification Writers: These values are not intended for use in preparing specifications.

CTM <sup>1</sup>	ASTM <sup>2</sup>	Property	Unit	Result		
		As supplied				
0176		Appearance		Non-slump paste		
		Color(s)		White, black, clear or aluminum		
0364		Extrusion rate <sup>3</sup>	g/minute	350		
0098		Skin-over time	minutes	7		
0095		Tack-free time	minutes	20		
		Mechanical properties, cured 7 days in air at 25°C (77°F) and 50% relative humidity				
0097B	D1475	Specific gravity		1.04		

- CTM: Corporate Test Method.
  ASTM: American Society for Testing and Materials.
- 3. Extrusion rate: 3.2 mm orifice at 0.62 MPa.

## Typical Properties (Cont.)

CTM	ASTM	Property	Unit	Result	
0099	D2240	Durometer hardness, Shore A		25	
0137A	D412	Tensile strength	MPa	2.3	
0137A	D412	Elongation at break	%	540	
0420		Volume coefficient of thermal expansion	1/K	1.12×10 <sup>3</sup>	
		Electrical properties, cured 7 days in air at 25°C (77°F) and 50% relative humidity			
0114	D149	Dielectric strength	kV/mm	21.6	
0112	D150	Dielectric constant at 100 Hz/100k Hz		2.8	
0112	D150	Dissipation factor at 100 Hz/100 kHz		0.0015	
0112	D150	Volume resistivity	Ohm.cm	1.5×10 <sup>15</sup>	

#### **How to Use**

#### **Substrate Preparation**

All surfaces must be clean and dry. Degrease and wash off any contaminants that could impair adhesion. Suitable solvents include isopropyl alcohol, acetone or methyl ethyl ketone.

Unprimed adhesion may be obtained on many substrates such as glass, metals and most common engineering plastics. Substrates to which good adhesion is normally not obtained include PTFE, polyethylene, polypropylene and related materials.

However, for maximum adhesion, the use of DOWSIL™ 1200 OS Primer is recommended. After solvent cleaning, a thin coat of DOWSIL™ 1200 OS Primer is applied by dipping, brushing or spraying. Allow primer to dry for 15 to 90 minutes at room temperature and a relative humidity of 50% or higher.

#### **How to Apply**

Apply DOWSIL™ 732 RTV Adhesive Sealant to one of the prepared surfaces, then quickly cover with the other substrate to be bonded.

On exposure to moisture, the freshly applied material will "skin-over". Any tooling should be completed before this skin forms. The surface is easily tooled with a spatula. The adhesive/sealant will be tack-free in less than 45 minutes.

#### **Cure Time**

After skin formation, cure continues inward from the surface. In 24 hours (at room temperature and 50% relative humidity) DOWSIL™ 732 RTV Adhesive Sealant will cure to a depth of about 3 mm. Very deep sections, especially when access to atmospheric moisture is restricted will take longer to cure completely. Cure time is extended at lower humidity levels.

Before handling and packaging bonded components, users are advised to wait a sufficiently long time to ensure that the integrity of the adhesive seal is not affected. This will depend on many factors and should be determined by the user for each specific application.

## Compatibility

DOWSIL™ 732 RTV Adhesive Sealant releases a small amount of acetic acid during cure. This may cause corrosion on some metallic parts or substrates, especially in direct contact or when the cure is carried out in a totally enclosed configuration which would not allow cure by-products to escape.

# Handling Precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

# Usable Life and Storage

Product should be stored at or below 32°C (90°F) in original, unopened containers.

As DOWSIL™ 732 RTV Adhesive Sealant cures by reaction with moisture in air, keep the container tightly sealed when not in use. A plug of used material may form in the tip of a tube or cartridge during storage. This is easily removed and does not affect the remaining contents.

## Limitations

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

## Health and Environmental Information

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, dow.com or consult your local Dow representative.

## Disposal Considerations

Dispose in accordance with all local, state (provincial) and federal regulations. Empty containers may contain hazardous residues. This material and its container must be disposed in a safe and legal manner.

It is the user's responsibility to verify that treatment and disposal procedures comply with local, state (provincial) and federal regulations. Contact your Dow Technical Representative for more information.

# Product Stewardship

Dow has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Dow products - from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

#### **Customer Notice**

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

Form No. 11-4225-01-0621 S2D

# How Can We Help You Today?

Tell us about your performance, design, and manufacturing challenges. Let us put our silicon-based materials experience, application knowledge, and processing experience to work for you.

For more information about our materials and capabilities, visit dow.com.

To discuss how we could work together to address your specific needs, go to **dow.com** for a contact close to your location. Dow has customer service teams, science and technology centers, application support teams, sales offices, and manufacturing sites around the globe.

dow.com

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

