



Building Sealant Recommendations and Surface Preparation Guide for Weatherseal Applications

Weatherseal

Dow has a full line of high-performance primers for sealants. Primers are used to enhance adhesion.

	DOWSIL™ 756 SM Building Sealant	DOWSIL™ 790 Silicone Building Sealant¹	DOWSIL™ 791 Silicone Weatherproofing Sealant	DOWSIL™ 795 Silicone Building Sealant
Substrate	Surface Prep			
Concrete and Masonry				
Brick	Limited Data/Field Test	No Primer	1200 OS/Primer P	Primer P
Concrete	Field Test	No Primer	1200 OS/Primer P	Primer P
Mortar	Primer P	No Primer	Primer P	Primer P
EIFS²				
All Manufacturers³	Limited Data/Field Test	Limited Data/Field Test	Limited Data/Field Test	Limited Data/Field Test
Stone				
Granite	No Primer	No Primer	Limited Data/Field Test	1200 OS/Primer P
Travertine	Limited Data/Field Test	Limited Data/Field Test	Limited Data/Field Test	Limited Data/Field Test
Marble⁴	1200 OS/Primer P	Limited Data/Field Test	Limited Data/Field Test	Limited Data/Field Test
Limestone⁸	1200 OS/Primer P	Limited Data/Field Test	Limited Data/Field Test	Primer P
(Natural Stone) Sandstone⁹	Limited Data/Field Test	Limited Data/Field Test	Limited Data/Field Test	Primer P
Paints				
Acrylic Latex	Limited Data/Field Test	Limited Data/Field Test	Limited Data/Field Test	Limited Data/Field Test
Duracron	No Primer	Limited Data/Field Test	No Primer	1200 OS/Primer P
Polyester Powder Coating⁷	Limited Data/Field Test	1200 OS	No Primer	No Primer
Polyurethane	Limited Data/Field Test	Limited Data/Field Test	Limited Data/Field Test	Limited Data/Field Test
Polyvinyl Chloride (PVC)	Limited Data/Field Test	Limited Data/Field Test	Limited Data/Field Test	Limited Data/Field Test
Fluoropolymer				
Kynar®	No Primer	Limited Data/Field Test	No Primer	Primer-C OS
Duranar®	No Primer	Limited Data/Field Test	No Primer	Primer-C OS
Duranar Sunstorm®	Limited Data/Field Test	Limited Data/Field Test	No Primer	Primer-C OS
Fluropon®	Limited Data/Field Test	Limited Data/Field Test	Limited Data/Field Test	Primer-C OS

DOWSIL™ 756 SM Building Sealant		DOWSIL™ 790 Silicone Building Sealant¹	DOWSIL™ 791 Silicone Weatherproofing Sealant	DOWSIL™ 795 Silicone Building Sealant
Substrate		Surface Prep		
Metals				
Aluminum – Chromate Conversion, Alodine®	No Primer	Limited Data/Field Test	No Primer	No Primer
Aluminum – Mill Finish	No Primer	1200 OS	1200 OS	1200 OS
Aluminum – Anodized	No Primer	1200 OS	No Primer	No Primer
Copper	Do Not Use	Do Not Use	No Primer	No Primer
Lead	Limited Data/Field Test	Limited Data/Field Test	Limited Data/Field Test	Limited Data/Field Test
Glass⁶				
Coated Glass	No Primer	1200 OS	No Primer	No Primer
Clear Glass	No Primer	No Primer	No Primer	No Primer
Steel				
Red Lead Primer	Limited Data/Field Test	Limited Data/Field Test	Limited Data/Field Test	Limited Data/Field Test
Weathered	Limited Data/Field Test	Limited Data/Field Test	Limited Data/Field Test	Limited Data/Field Test
Stainless	Limited Data/Field Test	Limited Data/Field Test	1200 OS	1200 OS
Galvanized	No Primer	1200 OS	No Primer	1200 OS/Primer P
Cold Rolled	Limited Data/Field Test	Limited Data/Field Test	Limited Data/Field Test	Limited Data/Field Test
Plastics				
PVC	Limited Data/Field Test	Limited Data/Field Test	1200 OS/Primer P	No Primer
Acrylic	Limited Data/Field Test	Do Not Use	Limited Data/Field Test	Limited Data/Field Test
Polycarbonate	Do Not Use	Do Not Use	Limited Data/Field Test	Limited Data/Field Test

Key: **1200 OS:** DOWSIL™ 1200 OS Primer; **Primer-C OS:** DOWSIL™ Primer-C OS; **Primer P:** DOWSIL™ Construction Primer P

Dow must test all materials for adhesion in structural applications.

Field adhesion tests must be performed at the jobsite to verify sealant adhesion.

¹ When using a primer with DOWSIL™ 790 Silicone Building Sealant, apply the primer before installing backer rod and allow the primer to dry. Cold weather and porous surfaces require additional drying time.

² Do not apply sealant to EIFS finish coat unless approved by EIFS manufacturer.

³ Cleaning procedures for EIFS systems should be followed.

⁴ The extremely porous nature of some marble, particularly white marble, can contribute to the potential for fluid migration into this substrate. Contact a Dow Specialist when working with marble.

⁵ Laminated glass with polyvinyl butyrol (PVB) interlayer may delaminate up to 1/4" at the edges when in contact with a sealant.

⁶ Do not use DOWSIL™ 790 Silicone Building Sealant on copper sputter coated glass.

⁷ See *Organic Solvent Usage* in the *Dow Americas Technical Manual* (62-1112) for comment.

⁸ Some limestone and other porous stone substrates contain iron and other impurities that can interact with DOWSIL™ 756 SM Building Sealant, causing discoloration of the sealant and/or substrate. Prior to use, DOWSIL™ 756 SM Building Sealant should be tested for compatibility with these substrates using water immersion.

This surface preparation guide is intended to aid in proper selection of surface preparation techniques and primers, if necessary, to gain adhesion that meets Dow's requirements. The suggestions in this guide are not blanket-approval recommendations; Dow requires all surface prep recommendations in this guide be verified by field or shop adhesion testing and documented prior to starting the project for each substrate/sealant combination. Failure to verify and document adhesion results may result in adhesion loss that is not covered by the Dow Warranty. Recommendations in this guide have been shown to be the best overall recommendations but do not cover every substrate for each material type or finish listed in this guide. Additionally, substrate manufacturers should be contacted to obtain recommendations for proper cleaning solvents for use with their materials. The entire *Weatherproofing* section of the *Dow Americas Technical Manual*, Form No. 62-1112, should be read and understood before proceeding with the evaluations. The following sections within the manual must be followed to verify and document adhesion:

- *Substrate Cleaning Procedure*
- *"Two Cloth" Cleaning Method*
- *Primer Application Procedure*
- *Field Adhesion Testing Procedure*
- *Field Adhesion Hand Pull Test Criteria*
- *Field/Shop Adhesion Log and Sealant Quality Control Logs*

Structural

All structural applications must be tested by the Dow test lab.

	DOWSIL™ 795 Silicone Building Sealant	DOWSIL™ 983 Structural Glazing Sealant	DOWSIL™ 995 Silicone Structural Sealant	DOWSIL™ 121 Structural Glazing Sealant
Substrate	Surface Prep			
Paints				
Acrylic Latex	Limited Data/Lab Test	Limited Data/Lab Test	Limited Data/Lab Test	Limited Data/Lab Test
Duracron	Primer-C OS	Primer-C OS	Primer-C OS	Primer-C OS
Polyester Powder Coat- ing ¹	Primer-C OS, 1200 OS	Primer-C OS, 1200 OS	No Primer	Primer-C OS
Fluoropolymer				
Kynar®	Primer-C OS	Primer-C OS, 1200 OS	No Primer	Primer-C OS
Duramar®	Primer-C OS	Primer-C OS	Primer-C OS	Primer-C OS
Duramar Sunstorm®	Primer-C OS	Primer-C OS	Primer-C OS	Limited Data/Lab Test
Fluoropon®	Primer-C OS	Primer-C OS	Primer-C OS	Limited Data/Lab Test
Metals				
Aluminum – Chromate Conversion, Alodine®	No Primer, 1200 OS	No Primer, 1200 OS	1200 OS	1200 OS
Aluminum – Anodized	No Primer	No Primer, 1200 OS	1200 OS	1200 OS
Glass – Surface to be Glazed to				
Clear	No Primer	No Primer	No Primer	No Primer
Float	No Primer	No Primer	No Primer	No Primer
Laminated ²	No Primer	No Primer	No Primer	No Primer
Plate	No Primer	No Primer	No Primer	No Primer
Tinted	No Primer	No Primer	No Primer	No Primer
Ceramic Frit Coating	No Primer	No Primer	No Primer	No Primer
Reflective Glass	No Primer	No Primer	No Primer	No Primer
Low E High (T) Glass	No Primer	No Primer	No Primer	No Primer

Key: **1200 OS**: DOWSIL™ 1200 OS Primer; **Primer-C OS**: DOWSIL™ Primer-C OS; **Primer P**: DOWSIL™ Construction Primer P; NA: Not applicable

Dow must test all materials for adhesion in structural applications.

Field adhesion tests must be performed at the shop or jobsite to verify sealant adhesion.

¹ See *Organic Solvent Usage* in the *Dow Americas Technical Manual* (62-1112) for comment.

² Laminated glass with polyvinyl butyrol (PVB) interlayer may delaminate up to 1/4" at the edges when in contact with a sealant

This surface preparation guide is intended to aid in proper selection of surface preparation techniques and primers, if necessary, to gain adhesion that meets Dow's requirements. The suggestions in this guide are not blanket-approval recommendations; Dow requires all surface prep recommendations in this guide be verified by field or shop adhesion testing and documented prior to starting the project for each substrate/sealant combination. Failure to verify and document adhesion results may result in adhesion loss that is not covered by the Dow Warranty. Recommendations in this guide have been shown to be the best overall recommendations but do not cover every substrate for each material type or finish listed in this guide. Additionally, substrate manufacturers should be contacted to obtain recommendations for proper cleaning solvents for use with their materials. The entire *Weatherproofing* section of the *Dow Americas Technical Manual*, Form No. 62-1112, should be read and understood before proceeding with the evaluations. The following sections within the manual must be followed to verify and document adhesion:

- *Substrate Cleaning Procedure*
- *"Two Cloth" Cleaning Method*
- *Primer Application Procedure*

For more information

Learn more about Dow's full range of building solutions, including service and support, at dow.com/buildingscience.

Dow has sales offices, manufacturing sites and science and technology laboratories around the globe. Find local contact information at dow.com/contactus.



Dow Building Science website:
dow.com/buildingscience



Contact Dow Building Science:
dow.com/customersupport

 **Visit us on X**
[@DowBScience](https://twitter.com/DowBScience)

 **Visit us on LinkedIn**
[Dow Building Science](https://www.linkedin.com/company/dow-building-science)

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

Dow has not performed architectural, engineering or other professional services in connection with any of the projects referenced herein, and Dow assumes no responsibility for any design, specifications, windload requirements, materials, samples, design elements, or testing of any design components, including the adequacy or completeness of the same, supplied or used by any party. Dow will only warrant products as set forth in a separate executed Dow warranty.

®™ Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow

© 2024 The Dow Chemical Company. All rights reserved.

2000024823-7220

Form No. 63-1184-01-0424 S2D